

Provision for Tear-Off Scrap Asphalt Shingles (01/11/2010)

DESCRIPTION

Tear-Off Scrap shingles (TOSS), as an asphalt binder source, may be included in plant mixed asphalt mixtures produced under specification 2360.

MATERIALS

Tear-Off Scrap shingles (TOSS) may be included in both mainline wear and non-wear courses to a maximum of 5 percent of the total weight of mixture. The percentage of TOSS used will be considered part of the maximum allowable RAP percentage (see Table 2360.3-B2a). Refer to Section 2360.2 G1 to select a virgin asphalt binder grade. The ratio of added new asphalt binder to total asphalt binder shall be 70% or greater ((added binder/total binder) x 100 >= 70). A minimum of 1 spotcheck per day per mixture blend is required to determine new added binder.

All TOSS materials shall be processed to meet with the following gradation requirements:

Gradation (% passing)	
Sieve Size (mm [inch])	(% passing)
12.5 [1/2 inch]	100
4.75 [#4]	90

The final product shall have no particle exceeding the maximum aggregate size allowed under Specification 2360. To conduct the gradation testing, a 500-700 gram sample of processed shingle material is air dried and then dry sieved over the 1/2" and #4 sieves and weighed.

Shingle asphalt binder content is to be determined by chemical extraction, MnDOT Lab Procedure 1852.

An aggregate bulk specific gravity (Gsb) of 2.650 may be used in lieu of determining the shingle aggregate Gsb by Mn/DOT 1205 (AASHTO T84).

Before a Mixture Design Report for a particular mixture is authorized, the following shall be submitted, along with materials and paperwork required by 2360.3:

- I. Certification by the processor of the shingle scrap, as to the shingle scrap content and source. Certification forms are located at the back of this provision and also available from the Bituminous Office.

Deleterious Materials

Scrap asphalt shingle shall not contain extraneous waste materials. Extraneous materials including, but not limited to, asbestos, metals, glass, rubber, nails, soil, brick, tars, paper, wood, and plastics shall not exceed 0.5 percent by weight as determined on material retained on the 4.75-mm (No. 4) sieve. To conduct deleterious material testing, a 500-700 gram sample of processed shingle material is sieved on the #4 sieve and any extraneous waste material is picked and weighed.

Reclaimed asphalt shingle shall contain less than the maximum percentage of asbestos fibers based on testing procedures and frequencies established by Mn/DOT, state or federal environmental regulatory agencies.

CONSTRUCTION REQUIREMENTS

TOSS shall be stockpiled separate from other salvage material. Blending of TOSS material in a stockpile with other salvage material is prohibited. Blending of a virgin sand material with the processed shingles, to minimize agglomeration of the shingle material, is allowed, but, the blended sand must be accounted for in the mixture design.

Tear-Off Scrap Shingle Certification Sheet
TEAR-OFF PROCESSOR

Project No: _____ **Project:** _____

Name: _____

Address: _____

Contact: _____

Phone: _____

We the undersigned certify that all of the asphalt shingle tear-off scrap is derived from non-regulated facilities such as private, pitched roof, residential “single family” re-roofing projects (e.g., buildings with up to four units per structure).

We certify that this shingle scrap material contains only shingles; no other material was added or introduced to this shingle scrap. We also certify the material contains no asbestos greater than the NESHAP threshold or other hazardous material¹. Additionally, we certify the TOSS meets MnDOT gradation and deleterious material requirements for processed shingle scrap.

Processor of Tear-Off Shingle Scrap Material

Date

Name of Contractor to Whom Processed Tear-Off Shingle Scrap Material Was Supplied

Supplier of Tear-Off Shingle Scrap:

Name: _____

Address: _____

Contact: _____

Phone: _____

¹Note: As determined by sampling in accordance with our MPCA approved Shingle Processing Management Plan and QA/QC Protocol