

Table 3138-5 Base and Surfacing Aggregate (containing more than 75 percent recycled concrete) Total Percent Passing*						
Sieve Size	Class 1	Class 3	Class 4	Class 5	Class 5Q	Class 6
2 in	—	100	100	—	100	—
1½ in	—	—	—	100		100
1 in	—	—	—		65 – 95	
¾ in	100	—	—	90 – 100	45 – 85	90 – 100
⅜ in	65 – 95	—	—	50 – 90	35 – 70	50 – 85
No. 4	40 – 85	35 – 100	35 – 100	35 – 80	15 – 45	35 – 70
No. 10	25 – 70	20 – 100	20 – 100	20 – 65	10 – 30	20 – 55
No. 40	10 – 45	0 – 8	0 – 8	0 – 8	0 – 8	0 – 8
No. 200	5.0 – 15.0	0 – 3.0	0 – 3.0	0 – 3.0	0 – 3.0	0 – 3.0

* Add letters in parentheses for each aggregate blend designating the type of recycled products included in the mixture.
 (B) = Bituminous, (C) = Concrete, (G) = Glass, (BC) = Bituminous and Concrete,
 (BG) = Bituminous and Glass, (CG) = Concrete and Glass,
 (BCG) = Bituminous, Concrete and Glass

3138.3 SAMPLING AND TESTING

Report the No. 200 sieve results to the nearest 0.1 percent and all other sieve results to the nearest 1 percent.

- A Sampling, Sieve Analysis and Crushing Tests Grading and Base Manual**
- B Los Angeles Rattler Loss Laboratory Manual Method 1210**
- C Shale Tests Laboratory Manual Method 1207 & 1209**
- D Bitumen Content Laboratory Manual Method 1852**
- E Insoluble Residue Laboratory Manual Method 1221**
- F Reclaimed Glass AGI Visual Method..... (AGI Data sheet 15.1 and 15.2)**

3139 GRADED AGGREGATE FOR BITUMINOUS MIXTURES

3139.1 SCOPE

Provide graded aggregate for use in bituminous mixtures.

3139.2 PLANT MIXED ASPHALT REQUIREMENTS

A Composition

Provide graded aggregate composed of any combination of the following sound durable particles as described in 3139.2B.

Do not use graded aggregate containing objectionable materials including:

- (1) Metal,
- (2) Glass,
- (3) Wood,
- (4) Plastic,
- (5) Brick, or
- (6) Rubber.

Provide coarse aggregate free of coatings of clay and silt.

Do not add soil materials such as clay, loam, or silt to compensate for a lack of fines in the aggregate.

Do not blend overburden soil into the aggregate.

Feed each material or size of material from an individual storage unit at a uniform rate.

Do not place blended materials from different sources, or for different classes, types, or sizes together in one stockpile unless approved by the Engineer as a Class E aggregate.

B Classification

B.1 Class A

Provide crushed igneous bedrock consisting of basalt, gabbro, granite, gneiss, rhyolite, diorite, and andesite. Rock from the Sioux Quartzite Formation may contain no greater than 4.0 percent non-Class A aggregate. Do not blend or add non-Class A aggregate to Class A aggregate.

B.2 Class B

Provide crushed rock from other bedrock sources such as carbonate and metamorphic rocks (Schist).

B.3 Class C

Provide natural or partly crushed natural gravel obtained from a natural gravel deposit.

B.4 Class D

Provide 100 percent crushed natural gravel produced from material retained on a square mesh sieve with an opening at least twice as large as Table 3139-2 allows for the maximum size of the aggregate in the composite asphalt mixture. Ensure the amount of carryover, material finer than the selected sieve, no greater than 10 percent of the Class D aggregate by weight.

B.5 Class E

Provide a mixture consisting of at least two of the following classes of approved aggregate:

- (1) Class A,
- (2) Class B, and
- (3) Class D.

B.6 Steel Slag

Steel slag cannot exceed 25% of the total mixture aggregate and be free from metallic and other mill waste.

The Engineer will accept stockpiles if the total expansion is no greater than 0.5 percent as determined by ASTM D 4792

B.7 Taconite Tailings

Obtain taconite tailings from ore mined westerly of a north-south line located east of Biwabik, Minnesota (R15W-R16W) or from ore mined in southwestern Wisconsin.

B.8 Recycled Asphalt Shingles (RAS)

Provide recycled asphalt shingles manufactured from waste scrap asphalt shingles (MWSS) or from tear-off scrap asphalt shingles (TOSS). Consider the percentage of RAS used as part of the maximum allowable Recycled Asphalt Pavement (RAP) percentage. See Table 3139-3.

B.8.A RAS Gradation..... MnDOT Laboratory Procedure 1801

Provide RAS in accordance with the following gradation requirements:

Table 3139-1 RAS Gradation	
Sieve size	Percent passing
½ in [12.5 mm]	100
No. 4 [4.75 mm]	90

B.8.B Binder Content

Determine the binder content using chemical extraction meeting the requirements of MnDOT Lab Procedure 1851 or 1852.

B.8.C Bulk Specific Gravity

The Contractor may use an aggregate bulk specific gravity (Gsb) of 2.650 in lieu of determining the shingle aggregate Gsb in accordance with MnDOT Lab Procedure 1205.

B.8.D Waste Materials

Do not allow extraneous materials including metals, glass, rubber, nails, soil, brick, tars, paper, wood, and plastics greater than 0.5 percent by weight of the graded aggregate as determined by material retained on the No. 4 [4.75 mm] sieve as specified in MnDOT Laboratory Procedure 1801.

B.8.E Stockpile

Do not blend an RAS stockpile with other salvage material. Do not blend MWSS and TOSS. The Contractor may blend virgin sand material with RAS to minimize agglomeration if the Contractor accounts for the blended sand in the final mixture gradation.

B.8.F Certification

Ensure the processor provides RAS certification on the following Department form “Scrap Asphalt Shingles from Manufacture Waste” or “Tear-Off Scrap Asphalt Shingles” at www.dot.state.mn.us/materials/bituminous.html

B.9 Crushed Concrete and Salvaged Aggregate

The Contractor may incorporate no greater than 50 percent of crushed concrete and salvaged aggregate in non-wear mixtures. Do not use crushed concrete in wearing courses.

B.10 Ash

Sewage sludge ash and waste incinerator ash are allowed as an aggregate source at a maximum of 5% of the total weight of the mixture. Sewage sludge ash for use as an aggregate source in wear or non-wear courses must be approved by examination with the Hazard Evaluation Process by MnDOT's Office of Environmental Stewardship.

B.11 Recycled Asphalt Pavement (RAP)**B.11.A Aggregate Angularity**

Provide combined RAP and virgin aggregates that meet the composite coarse and fine aggregate angularity for the mixture being produced.

B.11.B Objectionable Material

Do not use RAP containing objectionable materials including metal, glass, wood, plastic, brick, or rubber.

B.11.C Asphalt Binder Content

Determine the asphalt binder content using the MnDOT Lab Manual Method 1851 and 1852.

B.11.D Bulk Specific Gravity

Determine the bulk specific gravity in accordance with MnDOT Laboratory Procedure 1205 or 1815.

C Quality**C.1 Los Angeles Rattler Test MnDOT Laboratory Procedure 1210**

Ensure a coarse aggregate loss no greater than 40 percent.

C.2 Soundness (Magnesium Sulfate) MnDOT Laboratory Procedure 1219

Maximum loss after 5 cycles on the coarse aggregate fraction (material retained on No. 4 [4.75 mm] sieve for any individual source within the mix) as follows:

- (1) Percent passing the $\frac{3}{4}$ in [19 mm] sieve to percent retained on the $\frac{1}{2}$ in [12.5 mm] sieve, $\leq 14\%$,
- (2) Percent passing the $\frac{1}{2}$ in [12.5 mm] sieve to percent retained on the $\frac{3}{8}$ in [9.5 mm] sieve, $\leq 18\%$,
- (3) Percent passing the $\frac{3}{8}$ in [9.5 mm] sieve to percent retained on the No. 4 [4.75 mm] sieve, $\leq 23\%$,
- (4) For the composite if all three size fractions are tested, the composite loss $\leq 18\%$, and acceptance will be granted if:
 - (4.1) If the Contractor meets the composite requirement, but fails to meet at least one of the individual components, the Engineer may accept the source if each individual component is no greater than 110 percent of the requirement for that component.
 - (4.2) If the Contractor meets each individual component requirement, but fails to meet the composite, the Engineer may accept the source if the composite is no greater than 110 percent of the requirement for the composite.

Coarse aggregate that exceeds the requirements in this section for material passing the No. 4 [4.75 mm] sieve cannot be used.

C.3 Spall Materials and Lumps MnDOT Laboratory Procedure 1219

Stop asphalt production if the percent of spall or lumps measured in the stockpile or cold feed exceeds the values listed in Table 3139-3. Determine lump compliance by dry batching.

C.4 Insoluble Residue Test MnDOT Laboratory Procedure 1221

Use Statewide (except for District 6)

If using Class B carbonate materials ensure the portion of the insoluble residue passing the No. 200 [75 μ m] sieve is no greater than 10 percent.

Use for District 6 ONLY.

If crushed carbonate quarry rock (limestone or dolostone) is used, the minus #200 [75 μ m] sized portion of the rock insoluble residue shall not exceed 10% by weight.

Blending of sources and/or beds with an insoluble residue up to 15% is allowed to meet the 10% insoluble residue requirement. Individual beds thinner than 6 inches [150 mm] or up to 5% of the total face height, are exempt from the 15% maximum insoluble residue requirement. However, the aggregate producer shall practice good quality control at all times and exclude poor quality stone to the extent practical, regardless of the bed thickness and/or pocket size and location.

No carbonate quarry rock from the Platteville Geological Formation is allowed.

D Gradation

Ensure the aggregate gradation broad bands meet the following requirements in accordance with AASHTO T-11 (passing the No. 200 [75 μ m] wash) and AASHTO T-27.

Sieve size	A	B	C	D
1 in [25.0 mm]	—	—	100	—
¾ in [19.0 mm]	—	100*	85 – 100	—
½ in [12.5 mm]	100*	85 – 100	45 – 90	—
⅜ in [9.5 mm]	85 – 100	35 – 90	—	100
No. 4 [4.75 mm]	60 – 90	30 – 80	30 – 75	65 – 95
No. 8 [2.36 mm]	45 – 70	25 – 65	25 – 60	45 – 80
No. 200 [0.075 mm]	2.0 – 7.0	2.0 – 7.0	2.0 – 7.0	3.0 – 8.0

* The Contractor may reduce the gradation broadband for the maximum aggregate size to 97 percent passing for mixtures containing RAP, if the oversize material originates from the RAP source. Ensure the virgin material meets the requirement of 100 percent passing the maximum aggregate sieve size.

Aggregate Blend Property	Traffic Level 2	Traffic Level 3	Traffic Level 4	Traffic Level 5
20 year Design ESAL's	<1 million	1 - 3 million	3 - 10 million	10 – 30 million
Min. Coarse Aggregate Angularity (ASTM D5821) (one face / two face), %- Wear (one face / two face), %- Non-Wear	30/- 30/-	55 / - 55 / -	85 / 80 60/ -	95 / 90 80 / 75
Min. Fine Aggregate Angularity (FAA) (AASHTO T304, Method A) %- Wear %-Non-Wear	40 40	42 40	44 40	45 40
Flat and Elongated Particles, max % by weight, (ASTM D 4791)	-	10 (5:1 ratio)	10 (5:1 ratio)	10 (5:1 ratio)
Min. Sand Equivalent (AASHTO T 176)	-	-	45	45
Max. Total Spall in fraction retained on the #4 [4.75mm] sieve – Wear Non-Wear	5.0 5.0	2.5 5.0	1.0 2.5	1.0 2.5
Maximum Spall Content in Total Sample – Wear Non-Wear	5.0 5.0	5.0 5.0	1.0 2.5	1.0 2.5
Maximum Percent Lumps in fraction retained on the #4 [4.75mm] sieve	0.5	0.5	0.5	0.5
Class B Carbonate Restrictions				
Maximum% -#4 [-4.75mm] Final Lift/All other Lifts	100/100	100/100	80/80	50/80
Maximum% +#4 [+4.75mm] Final Lift/All other Lifts	100/100	100/100	50/100	0/100
Max. allowable scrap shingles–MWSS ⁽¹⁾ Wear/Non Wear	5/5	5/5	5/5	5/5
Max. allowable scrap shingles –TOSS ⁽¹⁾ Final Lift/All other Lifts	5/5	5/5	0/5	0/0

(1) MWSS is manufactured waste scrap shingle and TOSS is tear-off scrap shingle.

3139.3 PERMEABLE ASPHALT STABILIZED STRESS RELIEF COURSE (PASSRC) AND PERMEABLE ASPHALT STABILIZED BASE (PASB) REQUIREMENTS

A Restrictions

Do not use recycled materials including glass, concrete, bituminous, shingles, ash, and steel slag.

B Gradation

The Gradation limits are also considered the Job Mix Formula (JMF) limits.

B.1 PASB

Table 3139-4 PASB Aggregate Gradation	
Sieve Size	Percent Passing
1 ½ inch [37.5 mm]	100
1 inch [25.0 mm]	95 - 100
¾ inch [19.0 mm]	85 - 95
3/8 inch [9.5 mm]	30 - 60
No. 4 [4.75 mm]	10 - 30
No. 8 [2.36 mm]	0 - 10
No. 30 [600 µm]	0 - 5
No. 200 [75 µm]	0 - 3

B.2 PASSRC

Table 3139-5 PASSRC Aggregate Gradation	
Sieve Size	Percent Passing
5/8 inch [16.0 mm]	100
1/2 inch [12.5 mm]	85 - 100
3/8 inch [9.5 mm]	50 - 100
No. 4 [4.75 mm]	0 - 25
No. 8 [2.36 mm]	0 - 5

C Quality

Will meet all requirements of 3139.2.C.1 through 3139.2.C.3.

3139.2.C.4 changes to: If using Class B carbonate materials ensure the portion of the insoluble residue passing the No. 200 [75 µm] sieve is no greater than 10 percent.

D Mixture Quality Requirements

Table 3139-6 Mixture Aggregate Requirements for PASSRC & PASB	
Aggregate Blend Property	
Coarse Aggregate Angularity (ASTM D5821) (one face/two face) % PASSRC ⁽¹⁾ PASB ⁽¹⁾	95/ -65
Fine Aggregate Angularity (FAA) (AASHTO T304, Method A) %	NA
Flat and Elongated Particles, max(2) % by weight, (ASTM D 4791)	NA
Clay Content (2) (AASHTO T 176)	NA
Total Spall in fraction retained on the 4.75mm [#4] sieve	3.0
Maximum Spall Content in Total Sample	5.0
Maximum Percent Lumps in fraction retained on the 4.75mm [#4] sieve	0.5

Note (1) Carbonate Restrictions: If Class B (as defined in 3139.2.B.2), crushed carbonate quarry rock (limestone or dolostone), is used in the mixture, or if carbonate particles in the material retained on the 4.75 mm [No. 4] sieve exceeds 55 percent, by weight, the minus 0.075 mm [# 200] sieve size portion of the insoluble residue shall not exceed 10 percent.

3139.4 ULTRA THIN BONDED WEARING COURSE (UTBWC) REQUIREMENTS.

A Restrictions

Do not use recycled materials including glass, concrete, bituminous, shingles, ash, and steel slag.

B Quality

Will meet all requirements of 3139.2.C.

C Coarse Aggregate

Provide a Class A aggregate, as defined in 3139.2.B.1, in accordance with the following requirements:

Table 3139-7 UTBWC Coarse Aggregate Requirements		
Tests	MnDOT Laboratory Manual Method	Limit, %
Flat and elongated ratio at 3:1	1208	≤ 25
Los Angeles Rattler Test (LAR)	1210	≤ 40
Bulk Specific Gravity	1204	

D Fine Aggregate

Provide fine aggregate, passing the No. 4 [4.75 mm] sieve in accordance with the following requirements:

Table 3139-8 UTBWC Fine Aggregate Requirements		
Tests	Method	Limit, %
Sand equivalent*	AASHTO T 176	≥ 45
Uncompacted void content	MnDOT Laboratory Manual 1206	≥ 40
Bulk Specific Gravity	MnDOT Laboratory Manual 1205	

E Aggregate Gradation Broadband

Table 3139-9 UTBWC Aggregate Gradation Broadband	
Aggregate Size Typical application rates	3/8 inch [9.5 mm] 65-75 lbs/sy
Sieve Size	Gradation Broadband Limits % Passing
3/4 inch [19.0 mm]	
1/2 inch [12.5 mm]	100
3/8 inch [9.5 mm]	85 – 100
No. 4 [4.75 mm]	28 – 42
No 8 [2.36 mm]	21 – 33
No. 16 [1.18 mm]	14 – 24
No. 30 [600 µm]	9 – 20
No. 50 [300 µm]	6 – 15
No. 100 [150 µm]	5 – 11
No. 200 [75 µm]	3.0- 7.0

3139.5 MICRO-SURFACING REQUIREMENTS

A Restrictions

Do not use recycled materials including glass, concrete, bituminous, shingles, ash, and steel slag.

B Gradation

Provide a Class A aggregate or Taconite Tailings as defined in 3139.2.B.1, “Graded Aggregate for Bituminous Mixtures”, in accordance with the gradation requirements of Table 3139-10, “Micro-Surfacing Gradation Limits and QC Tolerances”.

The Contractor may use Class B aggregate blended with Class A aggregate or Taconite Tailings if using the following methods:

If blending aggregate types, ensure that material passing the 3/8 in [9.5 mm] sieve and retained on No. 16 [1.18 mm] sieve is at least 90 percent Class A, or Taconite Tailings, or both by weight.

Table 3139-10 Micro-Surfacing Gradation Limits and QC Tolerances Percent Passing (AASHTO T 11, AASHTO T 27)				
Sieve Size	Mn/DOT Type 1	Mn/DOT Type 2 ISSA* Type II	Mn/DOT Type 3 ISSA* Type III	QC TOLERANCES Percent in JMF for each sieve size
3/8 inch [9.5 mm]	100	100	100	—
No. 4 [4.75 mm]	100	90–100	70–90	±5.0
No. 8 [2.38 mm]	85–100	65–90	45–70	±5.0
No. 16 [1.18 mm]	72–92	45–70	28–50	±5.0
No. 30 [600 µm]	50–75	30–50	19–34	±5.0
No. 50 [300 µm]	35–55	18–30	12–25	±4.0
No. 100 [150 µm]	15–35	10–21	7–18	±3.0
No. 200 [75 µm]	5–15	5–15	5–15	±2.0
* International Slurry Surfacing Association				

C Quality

Provide aggregate that meets the durability requirements of Table 3139-11, "Micro-Surfacing Aggregate Durability Requirements".

Table 3139-11 Micro-Surfacing Aggregate Durability Requirements		
Tests on Aggregate	Test	Requirement, %
Sand equivalent	AASHTO T 176	≥ 60
Abrasion resistance*	AASHTO T 96	≤ 30
Soundness (using MgSO4)	AASHTO T 104	≤ 25
* Use Grading C for Type 3 material. Use Grading D for Type 1 & 2 material.		
Perform the soundness test on the Class B aggregate of the blend, if applicable.		

3139.6 SAMPLING AND TESTING

Perform sampling, sieve analysis, lumps, crushing, and shale testing meeting the requirements of the MnDOT Laboratory Manual.

3145 MINERAL FILLER

3145.1 SCOPE

Provide mineral filler as a soil or mixture component.

3145.2 REQUIREMENTS

A Composition

Provide a mineral filler of carbonate dust, Portland cement, hydrated lime, crushed rock screenings¹, fly ash, or rotary kiln dust.

¹ Crushed rock needs to have a stability and durability equivalent to those of the comparable mixture containing one of the other acceptable filler materials and be free of clay and shale.

B Gradation

The mineral filler will be finer than a #4 [4.75 mm] sieve and contain less than 25% of the material passing a #200 [75µm] sieve. The portion passing the #200 [75µm] sieve will meet the following gradation².

- Percent finer than 0.020 mm.....35 – 100
 - Percent finer than 0.005 mm.....10 – 40
 - Percent finer than 0.001 mm.....1 – 25
- ² Does not apply to Portland cement or hydrated lime

C Condition

Mineral filler which is to be added directly to the dried aggregate for the bituminous mixture will be thoroughly dry and free from lumps consisting of aggregates of fine particles. Crushed rock screenings used as mineral filler will be processed and handled in such a manner to prevent segregation and dried by passing through a dryer.

3145.2 SAMPLING AND TESTING

A Sample according to the Mn/DOT Bituminous Manual

B Fineness

B.1 Fine Aggregate Sieve Analysis according to Mn/DOT Laboratory Manual Method.... 1203

B.2 Particle Size Analysis of Soil according to Mn/DOT Laboratory Manual Method..... 1302