

SECTION 1007 AGGREGATE FOR BASE

1007.1 Scope. This specification covers aggregate to be used for base.

1007.2 Type 1 Aggregate.

1007.2.1 Type 1 aggregate for base shall consist of crushed stone, sand and gravel or reclaimed asphalt or concrete. The aggregate shall not contain more than 15 percent deleterious rock and shale. The fraction passing No. 40 sieve shall have a maximum plasticity index of six. Any sand, silt and clay and any deleterious rock and shale shall be uniformly distributed throughout the material.

1007.2.2 The aggregate shall be in accordance with the following gradation requirements:

Sieve	Percent by Weight
Passing 1-inch	100
Passing 1/2-inch	60-90
Passing No. 4	35-60
Passing No. 30	10-35

1007.3. Type 5 Aggregate.

1007.3.1 Type 5 aggregate for base shall consist of crushed stone, sand and gravel or reclaimed asphalt or concrete. The aggregate shall not contain more than 15 percent deleterious rock and shale. The fraction passing the No. 40 sieve shall have a plasticity index not to exceed six. Any sand, silt and clay, and any deleterious rock and shale shall be uniformly distributed throughout the material.

1007.3.2 Type 5 aggregate shall be in accordance with the following gradation requirements:

Sieve	Percent by Weight
Passing 1-inch	100
Passing 1/2-inch	60-90
Passing No. 4	35-60
Passing No. 30	10-35
Passing No. 200	0-15

1007.4. Type 7 Aggregate.

1007.4.1 Type 7 aggregate for base shall consist of crushed stone, sand and gravel, or reclaimed asphalt or concrete. The aggregate shall not contain more than 15 percent deleterious rock and shale. The fraction passing the No. 40 sieve shall have a plasticity index not to exceed six. Any sand, silt and clay, and any deleterious rock and shale shall be uniformly distributed throughout the material.

1007.4.2 Type 7 aggregate shall be in accordance with the following gradation requirements:

Sieve	Percent by Weight
Passing 1 1/2-inch	100
Passing 1-inch	70-100
Passing No. 8	15-50
Passing No. 200	0-12