


PREPARED BY
HIGHWAY PLANNING SURVEY
IN COOPERATION WITH
U.S. PUBLIC ROADS ADMINISTRATION

STATE OF MINNESOTA
DEPARTMENT OF HIGHWAYS
ROAD LIFE STUDIES
CONSTRUCTION PROJECT LOG RECORD

CONTROL SECTION 8202
TRUNK HIGHWAY 10
COUNTY Washington
DISTRICT 9A

LIMITS: Jct. T.H. 61 - W. End of Bridge (St. Croix River)



YEAR BUILT	PROJECT N ^o	DESCRIPTION			CODE N ^o		
		TYPE	WIDTH	THICKNESS			
		Oil Tr. Gravel	27'	3"	No Record of Const. Added in 1934.	1	2.93
1936	10-94-21	Br. 5473	30'		B.S. Underpass.	2	
M 1942	A.F.E. 4 A.F.E. 5	Patching & Bit. Seal Coat	24'		AE-1, 2788 Gal./Mi. Sand, 72 CY./Mi. Maint. Dept.	3	2.93
M 1945	A.F.E. 18	Gravel Lifts & Restore Bit. Mat (Spots)			MC3, 6749 Gal./Mi. Maint. Div.	4	2.93
C 1946	A.F.E. 20	Bit. Resurfacing Mixed Bit.	26'	1" added	SC3, 14318 Gal. Agg. 1538 C.Y.	5	1.93 2.93
M 1947	A.F.E. 5	Bit. Seal Coat	24'		AE-1, 8607 Gal. Agg. 245 C.Y.	6	2.93
M 1950	A.F.E. 4	Spot Treat. Bit. Surf. Repair	24'		MC3PRT-6, 7452 Gal. Agg. 465 C.Y.	7	2.93(Net 1.00)
M 1951	A.F.E. 4	Spot Treat. Bit. Surf. Repair	22'		MC3, 9362 Gal. Agg. 668 C.Y.	8	2.33(Net 1.20)
M 1952	A.F.E. 5	Light Bit. Seal	24'		RCS2, 4592 Gal. Agg. 136 C.Y.	9	2.93
C 1952	A.F.E. 48	Guard Rail				10	
M 1953	A.F.E. 604	Spot Treat. Bit. Surf. Repaire	22'		MC3, 8003 Gal. Agg. 605 Tons	11	2.93(Net 0.90)
M 1952	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'		MC3, 8653 Gal. Agg. 802 Tons	12	2.93(Net 0.85)
M 1956	A.F.E. 604	Bit. Surf. Repair	24'		MC3, 9129 Gal. Agg. 868 Tons	13	1.10
M 1957	A.F.E. 604	Spot Treat. Bit. Surf. Repair	24'		MC3, 3289 Gal. Agg. 230 Tons	14	2.93(Net 0.40)

YEARS		TOTAL MILES	UNINCORPORATED		INCORPORATED		RURAL		URBAN	
FROM	TO		RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.	RDWY. MI.	BR. MI.
1934		2.93	2.93	0.00	0.00	0.00	2.93	0.00	0.00	0.00

REMARKS: Layout is to scale as of 1934.

