

# 2016 SALT Schedule of Materials Control - Local Government Agency

This Schedule of Materials Control (SMC) outlines the minimum testing requirements for State Aid Funded and/or federal aid Projects off the National Highway and Trunk Highway System. Optional to this SMC is the MnDOT Materials Control Schedule. Usage of either schedule must be defined in the project proposal.

## **1603.2 SAMPLING AND TESTING - INSERT INTO SPECIAL PROVISIONS**

The first paragraph is hereby deleted and replaced with the following:

**Sampling and testing of materials for this project will be in accordance with the State Aid for Local Transportation (SALT) "Schedule of Materials Control – Local Government Agency" (SMC-LGA). The SMC-LGA establishes the size of samples and the minimum rate of testing. The SMC-LGA references the 2016 MnDOT Standard Specifications for Construction and does not set contract requirements for the material.**

The SMC - LGA serves as a guide for material testing with allowable acceptance "as directed by the Engineer" detailed in Specification 1501.1(1) - Authority of the Engineer. These testing rates are a minimum and additional tests may be taken at the Engineer's discretion. A minimal testing rate does not always ensure a quality product; field observations and attention to detail is crucial. Materials not listed on an approved products list may be sampled and tested as directed by the Engineer. Materials listed on a Qualified Products list may be accepted or tested at the discretion of the Engineer.

Federal Aid projects require Independent Assurance Inspection. Contact the MnDOT District IA Inspector when the job starts to provide the proper servicing of your project.

### **Definitions**

#### **[SALT Construction Website](#)**

MnDOT Office of State Aid for Local Transportation. The SMC - LGA is located at the construction page under "Information & Resources - Manuals".

#### **[MnDOT Schedule of Materials Control](#)**

Schedule of Materials Control (SMC) are inserted into project proposals to direct how materials are to be sampled. The SMC is updated yearly. Each SMC is project specific. Therefore, one needs to refer to their specific proposal.

#### **[Approved Products List](#)**

Products are "approved" when they have been found to routinely meet all applicable standards and specifications. The product is placed on the list based upon established successful manufacturer's quality control and warranties, but the listing may expire or require periodic renewal to verify the product has not changed over time. The approval process for the individual product should specify any expiration requirement.

#### **[Qualified Products List](#)**

Products are predicted to meet all applicable standards and specifications, but random sample testing is required to verify specific product lots meet specifications prior to usage. These products are generally considered to be "qualified" but not approved until tested for compliance. Successfully tested products lots are considered to be "approved". The approval process for the individual product should specify any further testing requirements for the product.

#### **[Certified Sources](#)**

Certified Sources must comply with each individual product's defined "certification procedure". Acceptance of products from certified sources follows the same sampling and testing as "qualified" products.

**Quality assurance (QA)** is a process-centered approach to ensuring that the best possible products or services are provided. Related to quality control, quality assurance focuses on enhancing and improving the process that is used to create the end result, rather than focusing on the result itself. Among the parts of the process that are considered in QA are planning, design, development, production and service.

**Quality control (QC)** is a process that is used to ensure a certain level of quality in a product or service. It includes actions deemed necessary to provide for the control and verification of certain characteristics of a product or service. It involves thoroughly examining and testing the quality of products or the results of services. The basic goal of quality control is to ensure that the products or services that are provided meet specific requirements and characteristics.

# Material Acceptance Summary

LOCAL NO. \_\_\_\_\_  
SAP/SP NO. \_\_\_\_\_

Bid Item #	Item Description	Qualified Product List	Approved Product List	Certificate of Compliance	Accepted by Engineer*
2105.604	Geotextile Fabric Type VI-A				
2105.604	Soil Stabilized Geogrid				
2357.606	Bituminous Tack Coat				
2357.606	Bituminous Tack Coat Shoulder				
2511.515	Geotextile Filter Type IV				
2540.601	Mailbox Support				
2540.602	Mailbox Support - temporary				
2573.502	Silt Fence - MS				
2573.505	Floatation Silt Curtain, still water				
2573.505	Sediment Control Log - wood fiber				
2574.508	Fertilizer type 3 & 4				
2575.502	Seed Mixtures				
2575.523	Erosion Control Blankets CAT 3				
2575.562	Hydraulic Matrix Type Bonded Fiber				
2575.571	Rapid Stabilization Method 3				
2580.603	Interim Pavement Marking				
2582.502	Paint - Pavement Marking				

\* Items not included on the Approved Product List or the Manufacturer's Certifications have not been received are hereby accepted by the Engineer. Materials on a Qualified Products list which have not been tested at the discretion of the Engineer are hereby accepted.

signed: \_\_\_\_\_  
Project Engineer                      Date

# Material Acceptance Summary

LOCAL NO. \_\_\_\_\_  
SAP/SP NO. \_\_\_\_\_

Bid Item #	Item Description	Qualified Product List	Approved Product List	Certificate of Compliance	Accepted by Engineer*

\* Items not included on the Approved Product List or the Manufacturer's Certifications have not been received are hereby accepted by the Engineer. Materials on a Qualified Products list which have not been tested at the discretion of the Engineer are hereby accepted.

signed: \_\_\_\_\_  
Project Engineer                                      Date

## BITUMINOUS QUALITY MANAGEMENT

The Contractor shall provide and maintain a quality control program as detailed in Specification 2360.2.G.  
The Engineer shall review the quality control program for compliance.

	Type of Test	Spec Section *	Contractor - QC Testing Rates	Agency - Testing Rates	
Start-Up Testing Rates for the 1st 2000 tons **	Bulk Specific Gravity	2360.2.G.7.b	1 test per 500 tons 55 lb. sample 3 full cylinder molds	1 Verification Mixture Sample test per day, all Verification samples are from a split (QC/QA) sample.	
	Maximum Specific Gravity	2360.2.G.7.c			
	Air Voids (calculated)	2360.2.G.7.d			
	Asphalt Content	2360.2.G.7.a			
	Adj. Asphalt Film Thickness (AFT)	2360.2.E.7.e			
	Gradation	2360.2.G.7.f			
	Fines to Effective Asphalt Ratio calc'd	2360.2.G.7.a/f			
	Coarse Aggregate Angularity (CAA)	2360.2.G.7.g	1 test per 1000 tons		
	Fine Aggregate Angularity (FAA)	2360.2.G.7.h			
	Added AC/Total AC Ratio (calc'd)	2360.2.G.7.a			
Production Testing Rates	Bulk Specific Gravity	2360.2.G.7.b	1 test per 1000 tons 55 lb. sample 3 full cylinder molds	1 Verification Mixture Sample test per day/ mix type, submit companion to the QC - CAA & FAA test results.	
	Maximum Specific Gravity	2360.2.G.7.c			
	Air Voids (calculated)	2360.2.G.7.d			
	Asphalt Content	2360.2.G.7.a			
	Adj. Asphalt Film Thickness (AFT)	2360.2.E.7.e			
	Gradation (minimum of 1 per day)	2360.2.G.7.f			
	Added AC/Total AC Ratio (calculated)	2360.2.G.7.a			
	Coarse Aggregate Angularity (CAA)	2360.2.G.7.g			NOTE 1
	Fine Aggregate Angularity (FAA)	2360.2.G.7.h			NOTE 2
	TSR	2360.2.G.7.i	When directed by the Materials Engineer		
	Aggregate Specific Gravity	2360.2.G.7.j	As directed by the Engineer		
	Mixture Moisture Content	2360.2.G.7.k	As directed by the Engineer		
	<a href="#">Asphalt Binder Certified Supplier</a>	2360.2.G.7.l	NOTE 3 (1qt. Steel container for asphalt binder. 1/2 gal. plastic container with wide screw top for emulsion)		
	<a href="#">Asphalt Emulsion Certified Supplier</a>	2357			
Compaction / Density Requirements	2360.3.D	Review special provisions			
Small Quantity Requirements	See 2360.2G.5 & 2360.3G				

Testing rates are minimums, additional testing is encouraged to ensure a quality product.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

\* Review Special Provisions & 2360.2.G Mixture Quality Management.

\*\* The testing rates apply only to mixtures that have not been tested on previous projects.

Mixtures from previous years should use the start-up testing rates.

NOTE 1: **At start-up or new Mix Design:** 2 tests per day for a minimum of 2 days, then 1 per day if CAA is met. If CAA > 8% of requirement, 1 sample per day but test 1 per week. No testing required for Class A and or B Aggregates.

NOTE 2: **At start-up or new Mix Design:** 2 tests per day for a minimum of 2 days, then 1 per day if FAA is met. If FAA > 5% of requirement, 1 sample per day but test 1 per week.

NOTE 3: Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer. Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly.

## BITUMINOUS SPECIALTY ITEMS

Type of Test	Spec	Contractor - QC Testing Rates	Agency - Testing Rates
<b>Gradation</b>	2363	1 per 1,000 Ton with a minimum 1 per day.	1 per day. 35 lbs.
PASSRC & PASB	3139.3		
Micro-Surfacing	2354 3139.5	Stockpile: 1/1,500 Tons (min 1/day) Machine Hopper: 1/500 Ton (min 1/day)	Stockpile & Machine Hopper: 1/day 30 lbs.
Seal Coat & Otto Seal	2356 3137.2 B	Stockpile: 1/1,500 Tons (min 1/day) Chip Spreader Hopper: 1/day	1/day from Hopper. 30 lbs.
<b>% Crushing - CAA</b>	2363	1 per 1,000 Ton with a minimum 1 per day.	1 per day from gradation test. 35 lbs.
PASSRC & PASB	3139.3		
<b>Moisture / Aggregate</b>	2354	Machine Hopper: 1/500 Tons (min 3/day)	1/day 2lbs
Micro-Surfacing	3139.5		
<b>Sand Equivalence</b>	2354	Stockpile or Machine Hopper: 1/500 Tons (min 1/day)	1/day, test at Engineer discretion, 25 lbs.
Micro-Surfacing			
<b>Flakiness Index</b>	2356	Sample taken from first load on first day, submit to Agency: 30 lbs.	Agency will test at their discretion, see Lab Manual 1223
Bituminous Seal Coat			
<b>Bituminous Mixture</b>	2356	1/300 Tons, min 1/day. %AC, Gradation, Max SpG, Adj.AFT	1/day, 20 lbs. 1 cylinder from truck box.
UTBWC	3151.2G		
PASSRC & PASB	3151 2350	Asphalt spot check: min 1/day	-
Stone Matrix Asphalt - SMA  Lab Manual 1203, 1204, 1205, 1211, 1214, 1806, 1807, 1808, 1813, 1853, 1854, 1855, AI SP-2 AASHTO T305	2365	<b>Tests</b> ,%AC,gradation,Gmm,Gmb, Voids,VMA,CAA,Draindown,VCA, fines/effective asphalt. Rate,(1/1000 tons, min.1/day)Agg SpG, mix moisture, TSR to be tested as directed by Engineer.  Submit companion 1 per day to agency: 3 full 6" by 12" cylinders	Tests: %AC, Gradation, Gmm,Gmb,Voids,VMA,CAA,VCA, fines/effective asphalt. Agency is not required to do draindown. Copy MDR to Project Engineer and Grading & Base Engineer.
<b>Asphalt Binder Tests</b>		<a href="#"><u>Asphalt Emulsion List</u></a>	<a href="#"><u>Asphalt Binder List</u></a>
UTBWC	2353 3151	Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer :  <b>Asphalt Binder:</b> First load, then 1/250,000 gallons. Sample size of 1 quart metal container. <b>Emulsified Asphalt:</b> First load, then 1/50,000 gallons. Sample size of 1/2 gallon wide screw top plastic container.	
Micro-Surfacing	2354		
Seal Coat & Otto Seal	2356		
Tack Coat	2357		
PASSRC & PASB	3151		
<b>Asphalt Binder Rate</b>	2354	Verify Application Rate 3/day	Verify Application Rate 1/day
Micro-Surfacing			
Fog Seal	2355	Verify Application Rate 1/day	Verify Application Rate 1/day
Seal Coat & Otto Seal	2356		
Bit Tack Coat	2357		

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

**Cold Inplace Recycling (CIR) & Stabilized Full Depth Reclamation (SFDR)**

Specification 2215

Test Type	Producer Testing Rates	Engineer Testing Rates	<a href="#">Grading &amp; Base Manual/Form</a>
Gradation SFDR (Simple) Pre-ground un-stabilized material	1 per mile - report sieves 2" & 3"	Run gradation at the discretion of the Engineer	.215 / 101 report sieve 2" & 3"
Gradation (Entire) (Material to be stabilized)	One per day, give split sample to the Engineer	Run gradation at the discretion of the Engineer	.215 / 101 report sieve 2", 1.5", 1.25", 1", 3/4", 3/8", #4, #10, #30.
Gradation (Simple) (Material to be stabilized)	1 per mile for SFDR & CIR w/o top size screening. 4 / mile for CIR with top size screens.	Run gradation at the discretion of the Engineer	.215 & .293 / 101 report sieve 2" & 1.5" for SFDR, 1.5" and 1.25" for CIR
Depth Check - Unstabilized and Stabilized	1 per 1,000' /machine width for each vertical machine face for initial pulverization and stabilization.	1 per day	.284 / 401
SFDR: Moisture during compaction of unstabilized portion	1/6,000 sq. yd.	none	.245 Speedy tester not allowed.
Penetration Index (DCP) - SFDR only Unstabilized.	1 per 1/2 mile lane mile	1 per lane mile	.255 / 205
Calibrate: mineral stabilizing agent application rate.	Once using design rate per vane feeder.	Observe contractor calibration	.286 or .287
Moisture: before injecting liquid bituminous material	1 per 5,000 feet of lane of daily anticipated SFDR & one after the addition of water by the Contractor or mechanical drying out (disking, etc).	none	.281 / 105
Yield: Mineral Stabilizing Agent and/or Liquid Bituminous Material	1 per transport load each type	1 per day each type	.286 & .287 / 402 & 403
Compaction: Nuclear density for SFDR stabilized and CIR	1 per 500 feet of lane width, <b>(see note below)</b> .	Observe the Contractor.	0.282
Control Strip: SFDR Stabilized and CIR	Minimum of once per project	Observe the Contractor.	
Bituminous Material Samples	none	Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer.	1 quart each sample
Mineral Stabilizing Agent Samples	none	1 sample	none
Foaming asphalt checks expansion ratio & half life	1 per load	Observe the Contractor once per day.	0.285
Moisture (stabilized) - before placement of next layer during curing.	none	3 daily after compaction.	Grading & Base Manual

Note: The Engineer may require a Contractor to perform additional nuclear density tests in areas that the Engineer believes are failing density requirements.

## GRADING AND BASE CONSTRUCTION ITEMS 1 of 3

		Material Type	Spec. *	Minimum Required Agency Acceptance Testing - QA	QC Testing Rates	Lab Sample	
Gradation Testing ( See Notes 2 & 3 )		Aggregate Surfacing	3138 2211.5	Total quantity less than 4000 tons (2200 cy-cv) = 1 gradation/1,000 tons (550 cy.cv) or less, determine compliance to individual results (table 2211-5). Total quantity greater than 4,000 tons (2200 cy-cv), divide the total quantity by 10,000, roundup to the next whole number to determine the number of lots. Each lot is divide into 4 equal sublots, randomly sample each subplot. Determine individual results and subplot averages for compliance (Table 2211-4 & 2211-5)	1 / 1,000 tons stockpile gradation only required for materials on hand. Spec 1906.2	1/source 30 lb.	
		Aggregate Base					
		Aggregate Shoulders					
		Drainable Aggregate Base (OGAB & DSB)	3136				
		Granular Borrow/Embankment	3149	1/40,000 Cubic Yards - Compacted Volume - CV	1/10,000 Cubic Yards - only required for material on hand, Spec 1906.2	1/source 30 lb.	
		Select Granular Borrow/Embankment					
		Modified Granular Borrow/Embankment					
		Stabilizing Aggregate					
		Full Depth Reclamation	3135		1/day	1/6,000 yd <sup>2</sup> & depth check	None
		Granular Filter	3149	1/ source	1/source - before delivery on the project.	1/source 30 lb.	
		Granular Backfill					
		Aggregate Backfill					
		Granular Bedding					
		Aggregate Bedding					
	Coarse Filter						
	Fine Filter						
Proctor	Non-Granular Material per 2105.3F	2105 2106 3149	1 per major soil, subgrade preparation specified density requires 100% of proctor density.	None	1 sample 25 lb.		
Sand Cone	Non-Granular Material per 2105.3F						
		<b>AGENCY TESTING: Roadway Embankment:</b> One test per 4,000 yd <sup>3</sup> (CV) <u>or</u> if test rolled, One test per 8,000 yd <sup>3</sup> (CV), <b>Transverse culverts &amp; Abutments:</b> 1 test per every 2 feet of fill per 250' of trench length. <b>Structures Trenches:</b> One test/500 feet of each structure length at various depths. <b>Subgrade Preparation:</b> One per 25 road stations.					
Penetration Index Method (DCP) Index *	Aggregate Base	3138	1 DCP tests per 500 yd <sup>3</sup> (CV) or 1 per 900 Tons. If test rolled, 1 test / 1,000 yd <sup>3</sup> (CV) or 1,800 Tons.	None	None		
	Aggregate Shoulders						
	Full Depth Reclamation	3135	1 DCP test per 3,000 yd <sup>2</sup>				
	Granular Materials Subgrade Preparation (for materials meeting 3149.2B1)	3149.2 B	<b>AGENCY TESTING: Roadway Embankment:</b> One test per 2,000 yd <sup>3</sup> (CV) <u>or</u> if test rolled, One test per 4,000 yd <sup>3</sup> (CV), <b>Transverse culverts &amp; Abutments:</b> 1 test per every 5 feet of fill per 250' of trench length. <b>Structures Trenches:</b> One test/500 feet of each structure length at various depths. <b>Subgrade Preparation:</b> One per 25 road stations.				

[The Grading and Base Manual allows the nuclear density gauge, see pages 60 and 65.](#)

## GRADING AND BASE CONSTRUCTION ITEMS 2 of 3

	Material Type	Spec. *	Minimum Required Agency Acceptance Testing - QA	QC Testing Rates	Lab Sample
Moisture Content Test During All Compaction Methods	*Aggregate Base, Shoulder & Surfacing	3138	1 per project unless directed by the Engineer, obtain split companion sample for the Contractor. * May replace tests with time stamped photos showing water being applied.	1 / 1,000 yd <sup>3</sup>	None
	Drainable Aggregate Base (OGAB & DSB)				
	Full Depth Reclamation	3135		1/6000 yd <sup>2</sup>	
	All Embankment Materials	3149 2105		1/10,000 yd <sup>3</sup>	
	Subgrade Preparation			1 per 25 road stations	
Percent Crushing	Particle Count ( note 1 )	1/ source unless directed by Engineer, (required for 3138.2B & C, 3149.2C & G1, 3136.2B Drainable Bases).		1 required for mat'l on hand, Spec 1906.2	1/source 30lb
Quality	Aggregate Quality Tests	3138 3149 3601	1/ source unless directed by Engineer	2 required for mat'l on hand, Spec 1906.2	1/source 30lb
Depth Check	Full Depth Reclamation		1 per day unless directed by Engineer	1/1,000 feet of machine width.	
Test Rolling	Test Rolling (as directed in the special provisions)	2111	As directed by the Engineer the contractor will perform test rolling at the top of all subgrade, base layers (2211), non stabilized FDR (2215) and granular layers not meeting the requirements of 3149.2B2 (2105 & 2106). Minimum 12' width and 300' length. Agency to observe test rolling. See G & B Manual 5-692.270.		

**Laboratory Samples are companion split samples to the QA sample:**

1. Companion gradation, proctor, QA crushing, aggregate quality samples not required 1,000 tons or less.
2. Include the laboratory companion with the first field sample.
3. Include the field sample results with the laboratory sample.
4. Laboratories with AMRL Accreditation are not required to submit laboratory companion samples.
5. Carbonate aggregate materials require 50 lb. samples for the laboratory testing.

NOTE 1: Percent crushing test is not required when the material is crushed from a quarry or contains 25% or greater recycled materials.

NOTE 2: Submit a laboratory companion to the first Acceptance Gradation sample for a bituminous extraction, see 3138.2C. Full Depth Reclamation samples are not required.

NOTE 3: The Certification of Aggregates and Granular Materials procedure and documentation of testing locations is at the discretion of the Engineer.

\* Review the Special Provisions. For granular materials, aggregate compaction will be by the "Penetration Index Method" unless otherwise designated in the Special Provisions. Other compaction methods include the "Specified Density Method" (sand cone), "Quality Compaction Method" or "Light Weight Deflectometer Method. See 2211.3.D.2 Compaction. The Grading and Base Manual allows the nuclear density gauge, see pages 60 and 65.

Conversions: 1 ton = 0.55 yd<sup>3</sup> (CV), 1 ton = 0.7 yd<sup>3</sup> (LV), 1 yd<sup>3</sup> (CV) = 1.8 tons.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

Samples are not required for less than 500 tons (275 yd<sup>3</sup>).



## GRADING AND BASE CONSTRUCTION ITEMS 3 of 3

### Guidelines for Required Crushing & Aggregate Quality Tests

	<b>3149</b> Granular Materials	<b>3138</b> Aggregate for Surface and Base	<b>3136</b> Drainable Bases
Crushing	<b>Yes</b> , for Stabilizing Aggregate, Fine Aggregate Bedding and Medium Filter Aggregate. Test waived if material contains recycled at twice the minimum crushing requirement. Not required for quarried sources.	<b>Yes</b> , for Class 5, 5Q & 6. Test waived if material contains recycled at twice the minimum crushing requirement. Not required for quarried sources. Class 2 must contain 100% crushed quarry rock.	<b>Yes.</b> Not required for quarried sources.
Bitumen Content	<b>Yes</b> , if it contains Bitumen	<b>Yes</b> , if it contains Bitumen	Not applicable
LAR	Not applicable	<b>Yes</b> , if source is carbonate quarry and does not contain bitumen.	<b>Yes</b>
Insoluble Residue	<b>Yes</b> , if source is carbonate quarry and does not contain bitumen.	<b>Yes</b> , if source is carbonate quarry and does not contain bitumen.	<b>Yes</b> , if source is carbonate quarry.
Litho Exam & Shale Float Test	<b>Yes</b> , for Medium Filter Aggregate	<b>Yes</b> , for Class 3, 4, 5, 5Q & 6, when not from quarried rock, and does not contain bitumen.	<b>Yes</b> , when not from a quarried source.

[Click here for testing procedures in the Grading & Base Manual.](#)

[Forms and worksheets at the Grading & Base Website.](#)

[Gradation worksheets at the SALT Construction Website](#)

## CERTIFIED READY-MIX CONCRETE, 1 of 2

The Prime Contractor is responsible to assure that all ready-mix concrete used is produced by an annually Certified Ready-Mix plant as detailed in Specification 2461.3F.

Material Spec.	Test Type <a href="#">(Concrete Manual)</a>	Producer QC Testing Rates	Engineer Testing Rates ( 1 ) Verification-companion to QC			<a href="#">Form</a>		
bridge 2406.2 2411.2 2461.2 2461.3 general 2301** 2452.2 2461.2 2461.3 2506.2 2511.2 2514.2 2520.2 2521.2 2531.2 2533.2 2545.2 2554.2 2557.2 2564.2 2565.2	Concrete Plant Production Testing Rates *	Gradation (5-694.145) (5-694.148)	Coarse & Fine: When over 20 yd3 per week, 1 per week or 1 per 400 yd3, whichever is greater. <u>Bridge Deck Concrete</u> must have passing gradations prior to mixing.		Coarse & Fine: 1 per week			
		Moisture Content (5-694.142)	1 every 4 hours		None			
		Aggregate Quality (5-694.146)	Engineer Testing Rates: Minimum of 1 per project per each fraction - use of MnDOT test results for the same 30 day time period is acceptable. <u>For bridge concrete</u> : 1 test each fraction per month. <u>For all bridge deck concrete poured during the month</u> : Test monthly quality to 3137.2D2 for each coarse aggregate fraction. Designate 3137.2D2 on the sample card. Gradation results will be included with the monthly quality tests.					
		Coarse Aggregate (% Passing 200) (5-694.146)						
		Minimum Aggregate Sample Size *companion required, double sample size						
		Aggregate Size	Gradation*	Quality*	Moisture	% -200 C.Ag		
		3/4" Plus, #4	25 lb.	50 lb.	2000 g	10 lb.		
		3/4" Minus, #67	25 lb.	30 lb.	2000 g	6 lb.		
		#7, CA-70	6 lb.	30 lb.	2000 g	6 lb.		
		CA-80, #89	1.1 lb. (500 g)	30 lb.	500 g	-		
		Fine Aggregate	1.1 lb. (500 g)	30 lb.	500 g	-		
		Concrete Field Testing Rates	<u>Sampling Locations for Air, Slump, Temperature and Cylinder Testing</u>					2448 Weekly Concrete Report
(1) First load each day per mix - Take sample after discharging approximately 1/4 yd3, stop further discharge until both slump and air content test are completed. The first load of concrete must have <span style="color: red;">passing</span> air content and slump <span style="color: red;">prior to placement</span> . Cast strength specimens from the same load as the air content and slump test. Test whenever adjustments are made to the mix.								
(2) Subsequent tests - Sample from the middle portion of the load.								
Test Type	Engineer Testing Rates ( 1 )							
Air Content - Type 3 Concrete (5-694.541)	1 test per 200 yd3. <u>For Bridge Concrete</u> : 1 test per 100 yd3. Test first load each day per mix. Test when adjustments are made to the mix.							
Slump (5-694.531)	1 test per 200 yd3. <u>For Bridge Concrete</u> : 1 test per 100 yd3. Test first load each day per mix, or as necessary to verify passing slump. Not required for slip form placement.							
Air and Concrete Temperature (5-694.550)	Record temperature each time air content, slump or compressive strength specimen is performed/fabricated.							

( 1 ) - Review the requirements of 2461.3F Certified Ready-Mix Concrete, 2461.3G Concrete Placement and 5-694.010 Inspector's Checklist in the Concrete Manual.

\*Small quantity is 25 yd3 or less per week with no gradation testing or plant monitoring required but remember that **Concrete Field Testing is required.**

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

## CERTIFIED READY-MIX CONCRETE, 2 of 2

The Prime Contractor is responsible to assure that all ready-mix concrete used is produced by an annually Certified Ready-Mix plant as detailed in Specification 2461.3F.

Spec.		Test Type	Engineer Testing Rates ( 1 )	Form
See page 1 of 2	Concrete Field Testing Rates	Compressive Strength (5-694.511) Standard cylinder size is 4 x 8, use 6 x 12 with aggregate greater than 1 1/4".	General Concrete Grades F, G, M, P, and R: 1 set of 3 cylinders per 300 yd3.	2409 Concrete Cylinder
			Bridge Concrete Grades B, S, and Y: 1 set of 3 cylinders per 100 yd3, then 1 set of 3 cylinders per 300 yd3	
			Agency will break 1 set of 3 cylinders at 28 days. Agency will cast up to 3 control cylinders, any additional control cylinders are the responsibility of the Contractor.	
			Cellular Concrete: 1 set of 4 cylinders (28 days) per day, fill in 2 equal lifts, <i>do not rod</i> , lightly tap the sides, cover and move to area with no vibration. Do not disturb for 24 hours.	
				Concrete Pavement Thickness **
		Flexural Strength	Producer: 1 beam (28 day) per day. Make additional control beams as necessary. Control beams shall be made within the last hour of concrete poured each day. Fabricate beams, deliver beams to curing site, and clean beam boxes. Cylinders may be substituted for beams at the discretion of the Engineer.	2162 Concrete Test Beam Data
		Concrete Pavement Texture	Producer: 1 per 1000 lineal feet per lane of concrete pavement at locations determined by the Agency. The Contractor supplies all materials necessary to perform the required testing.	MIT SCAN T2 Report

( 1 ) - Review the requirements of 2461.3F Certified Ready-Mix Concrete, 2461.3G Concrete Placement and 5-694.010 Inspector's Checklist in the Concrete Manual.

\*Small quantity is 25 yd3 or less per week with no gradation testing or plant monitoring required but remember that **Concrete Field Testing is required.**

\*\*Concrete Pavement: Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly.

The testing rates shown in the SMC - LGA are minimums. Take as many tests as necessary to ensure quality concrete. It is recommended that the Agency Plant Monitor be present during critical pours, such as superstructure or paving concrete. If any field test fails, reject the concrete or if the Producer makes adjustments to the load to meet requirements, record the adjustments on the Certificate of Compliance and Weekly Concrete Report. Retest the load and record the adjusted test results. Make sure the next load is tested, before it gets into the work. If batching adjustments are made at the plant, test the adjusted load, before it gets into the work. Continue to test the concrete when test results are inconsistent or marginal. Material not meeting requirements shall not knowingly be placed in the work. If failing concrete inadvertently gets placed in the work, use either the MN/DOT Standard Specifications for Construction or the Schedule of Price Reductions for Concrete to address penalties. It is recommended that the Agency representative continually monitor the progress of all concrete pours. (It is not a recommended practice to only perform minimum testing requirements and leave the project.)

## Concrete Plant and Field Materials

All materials must come from certified or qualified sources. All certified source must state so on the delivery invoices. The most current list of certified/approved sources can be found at MnDOT Material Website. Materials listed on the Approved Products List do not have to be sampled and need to be listed on the Material Acceptance Summary detailed in the SALT SMC. Samples can be submitted as directed by the Engineer.

	Material	Spec. No.	Minimum Required Field Sampling Rate	Form No.
Concrete Plant Batching Materials	Portland Cement	3101	Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer. For certified ready-mix and concrete paving sample rates: 1 sample when the plant is certified. Take additional samples at 6 months if producing Agency concrete, if the plant changes sources or as the contract requires. The producer obtains a 5 lb. sample and stores the sample in a sealed container provided by the Agency and includes the suppliers delivery invoice from which the sample is obtained.	24300 ID Card Cement Samples
	Slag	3102		
	Blended Cement	3103		
	Fly Ash	3115		24308 Fly Ash
	Admixtures (Accelerationg, Retarding, Water-Reducing, Air- Entraining, etc.)	3113	For all concrete: 1 sample in a 1/2 pint plastic container provided by the Agency when the plant is certified. Take additional samples at 3 months if producing Agency concrete, if the plant changes sources or as the contract requires.	2410 Sample ID Card
	Water	3906	1 sample in a 1 gallon clean glass or plastic container from a questionable source.	
Concrete Field Materials	Preformed Joint Filler	3702	Visual Inspection, sample size 2 sq.ft.	2410 Sample ID Card
	Preformed Elastomeric Type	3721	1 per lot. Only materials from a qualified sources. <a href="#">Link to Approved Products List.</a>	
	Silicone Joint Sealer	3722		
	Hot Poured Elastomeric Type	3723 3725		
	Burlap	3751	Visual Inspection	
	Paper	3752	Visual Inspection - Must be white opaque.	
	Membrane Curing Compound	3754 3754AMS 3755	Visual Inspection - Use only pre-approved curing compounds.	
	Plastic	3756	Visual Inspection - Must be white opaque and free from holes.	
Refer to the "Metals" schedule for sampling requirements for concrete reinforcement.				

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly.

## 2301 CONCRETE PAVEMENT - AGENCY 1 of 2 \*

Test Type (concrete manual)	Spec.	Concrete Paving Batch Plant Agency Testing	Certified Ready-Mix Plant Agency Testing	<a href="#">Form</a>
Gradation (1) (5-694.145) (5-694.148)	3126 3137	Test the first 4 QA samples of production each time the Contractor mobilizes the plant in a calendar year or changes aggregate sources.		21764 Agg Work sheet
		1 per day randomly thereafter.	1 per 1000 yd <sup>3</sup> or 1 per week whichever is higher, randomly.	
Aggregate Moisture - QC Verification (2) (5-694.142)	3126 3137	If w/c incentives apply: 1 per 1000 yd <sup>3</sup> or every 4 hours, whichever is greater. Take initial sample within the first 250 yd <sup>3</sup> .	If w/c incentives apply: 1 per 200 yd <sup>3</sup> or every 4 hours, whichever is greater. Take initial sample within the first 100 yd <sup>3</sup> .	Concrete W/C Ratio Work sheet
Water Content, Microwave Oven Verification (3) (5-694.532)	<a href="#">Concrete Manual</a>	Take initial sample within the first 250 yd <sup>3</sup> . At least one additional verification test should be taken if more than 1000 yd <sup>3</sup> is produced in a day.	Take initial sample within the first 100 yd <sup>3</sup> . At least one additional verification test should be taken if more than 400 yd <sup>3</sup> is produced in a day.	
Coarse Aggregate, -200 sieve (5-694.146)	3137	1 randomly selected sample on the first day of production and each time the Contractor mobilizes the plant, changes the aggregate sources, or the cleanliness of the coarse aggregate is in question, then 1 per week randomly thereafter. -200 test may be performed at the lab instead at the plant at the discretion of the Engineer.		21764 Agg Work sheet
Coarse and Fine Aggregate Quality (4)	3126 3137	During concrete production: 1 randomly selected test each fraction every 20,000 yd <sup>3</sup> of production. Split the Quality sample 4 ways: 1) Provide 2 quarters of the sample to the producer/contractor. 2) Test the -200 on the coarse aggregate at the plant the day it was sampled. 3) Submit the remaining sample to the lab for quality testing including testing the -200 sieve on the coarse aggregate.		2410 Sample ID Card
Alkali Silica Reactivity (ASR) Testing	2301	1 per paving project per sand source. Provide one 5 lb. sample of: cement, supplementary cementitious material (fly ash or slag), and sand. Write "Project Specific ASR Testing" on all 3 sample cards. <b>ASR Testing is not required if the entire project is less than 3,500 cubic yards.</b>		2410 24300 24308
Coarse Aggregate Quality Testing of Incentive / Disincentive	3137	<b>If coarse aggregate quality incentives apply:</b> Test the Class B aggregates for % absorption and Class C aggregates for % carbonate including any other test necessary to make those determinations. Sample the 2 largest fractions in accordance with the following table and 2301:		Coarse Agg Quality Incent / Disincent Work sheet
		<b>Coarse Aggregate Quality Incentive/Disincentive Sampling Rates</b>		
		Plan Concrete Cubic Yards	Samples per fraction	
		3,500 - 7,500	3	
		7,501 - 10,000	5	
		10,001 - 25,000	10	
		25,001 - 50,000	15	
50,001 +	20			

\*Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly. Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

**2301 CONCRETE PAVEMENT - AGENCY 2 of 2**

Test Type	Spec.	Concrete Field Testing - Agency	Form
Air Content before consolidation for Type 3 concrete	<a href="#">Review Concrete Manual Website</a>	1 correlation air test per day	2448 Weekly Concrete Report
Air Content after consolidation for Type 3 concrete		1 air test per day	
Slump		<b>For fixed form placement:</b> 1 slump test per day. <b>For slip form placement:</b> No slump testing required.	
Concrete Temperature		Record temperature each time air content, slump or strength test specimen is performed/fabricated by the Agency.	
Flexural Strength		Supply beam boxes, cure, and test beams. MnDOT standard beam box size is 6" x 6" x 20" unless other sizes or types are approved by the Concrete Engineer.	2162 Test Beam Data
Concrete Pavement Texture		Determine texture testing locations using random numbers.	Probing, Coring, Texture and MIT-Scan T2 Report
Thickness		Determine probing and coring locations using random numbers. Initial pavement at core locations and re-initial the sides of specimens after coring to clearly verify their authenticity.	Concrete Profile Summary Work Sheet
Surface Smoothness			None

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

**NOTE (1):** All gradation samples shall be taken in the presence of the Agency, unless otherwise authorized by the Engineer. All samples shall be taken off the belt leading to the weigh hopper unless otherwise approved by the Engineer. All gradations and quality tests require companion samples. If Coarse Aggregate Quality Incentive / Disincentives apply: The Agency may also use the QA samples for incentive / disincentive testing. Notify the producer to double the QC/QA sample size. **If well-graded aggregate incentives apply:** Use the Contractor's gradation results for well-graded aggregate incentive calculations as verified by Agency testing. Use the Well-graded Concrete Agg Worksheet.

**NOTE (2): If w/c incentives apply:** Use aggregate moisture results for determining the water content to calculate the w/c incentive / disincentive. Use the Concrete W/C Ratio Calculation Worksheet and do not leave sample unattended.

**NOTE(3): If w/c incentives apply:** Microwave oven verification testing to verify the w/c ratio is completed in conjunction with Agency aggregate moisture testing. Do not leave samples unattended.

**NOTE (4):** Prior to concrete production: Obtain pre-production samples for quality testing at least 16 hours prior to concrete production. Samples may be taken from the stockpile and -200 test may be performed at the lab instead at the plant at the discretion of the Engineer. If the entire project is <3,500 yd<sup>3</sup>, pre-production sampling is not required.

Minimum Aggregate Sample Size *companion required, double sample size				
Aggregate Size	Gradation*	Quality*	Moisture	% -200 C.Agg
3/4" Plus, #4	25 lb.	50 lb.	2000 g	10 lb.
3/4" Minus, #67	25 lb.	30 lb.	2000 g	6 lb.
#7, CA-70	6 lb.	30 lb.	2000 g	6 lb.
CA-80, #89	1.1 lb. (500 g)	30 lb.	500 g	-
Fine Aggregate	1.1 lb. (500 g)	30 lb.	500 g	-

**CONCRETE PAVEMENT - PRODUCER / CONTRACTOR 1 of 2\***

Test Type (concrete manual)	Spec.	Concrete Paving Batch Plant Production Testing	Certified Ready-Mix Plant Production Testing	
Gradation (1) (5-694.145) (5-694.148)	3126 3137	When over 250 yd <sup>3</sup> produced per day: 1 per 1500 yd <sup>3</sup> , or completed 1 per 1/2 day, whichever is the higher sampling rate.	When over 20 yd <sup>3</sup> produced per day: 1 per 400 yd <sup>3</sup> , or completed every 4 hours, whichever is the higher sampling rate.	
Coarse Aggregate -200 sieve (5-694.146)	3137	Test the first sample then at least 1 of the next 3 samples on the first day of production and each time the Contractor mobilizes the plant, changes the aggregate sources, or the cleanliness of the coarse aggregate is in question, then 1 per day randomly thereafter. Test these samples at the plant.		
Aggregate Moisture QC Verification (2) (5-694.142)	3126 3137	If w/c incentives do not apply: 1 per 1000 yd <sup>3</sup> , or 1 completed every 4 hours, whichever is the higher sampling rate.	If w/c incentives do not apply: 1 completed every 4 hours.	
Water Content, Microwave Oven Verification	<a href="#">Review Concrete Manual</a>	If w/c incentives apply: Obtain the plastic concrete sample at the plant. See Concrete Manual (5-694.532)		
Unit Weight QC		Test one load of concrete per day at the plant. See Concrete Manual (5-694.542)		
Air Content QC (5-694.541)		Test the first load of concrete at the plant		
Coarse and Fine Aggregate Quality	3126 3137	Prior to concrete production: Test the Agency's pre-production sample at the Contractor's discretion. During concrete production: Test the -200 on the quality companion sample the day it was sampled. All other testing is at the Contractor's discretion.		
Coarse Aggregate Quality Testing for Incentive / Disincentive	3137	Test at the Contractor's discretion.		
Minimum Aggregate Sample Size *companion required, double sample size				
Aggregate Size	Gradation*	Quality*	Moisture	% -200 C.Agg
3/4" Plus, #4	25 lb.	50 lb.	2000 g	10 lb.
3/4" Minus, #67	25 lb.	30 lb.	2000 g	6 lb.
#7, CA-70	6 lb.	30 lb.	2000 g	6 lb.
CA-80, #89	1.1 lb. (500 g)	30 lb.	500 g	-
Fine Aggregate	1.1 lb. (500 g)	30 lb.	500 g	-

\* Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

**NOTE (1):** Performing testing on representative material at the end of the most recent day of production is allowed. If well-graded aggregate incentives apply: Use the Contractor's gradation results for well-graded aggregate incentive calculations as verified by Agency testing.

**NOTE (2):** Complete the initial moisture content and adjust the batch water prior to the start of concrete production each day. If weather conditions allow, performing moisture testing on representative material at the end of production the prior evening is allowed.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

**CONCRETE PAVEMENT - PRODUCER / CONTRACTOR 2 of 2**

Test Type	Spec.	Concrete Field Testing - Contractor
Air Content before consolidation for Type 3 concrete	<a href="#">Review Concrete Manual Website</a>	1 per 300 yd <sup>3</sup> or 1 per hour, whichever is less. Test first load each day per mix.
Air Content after consolidation for Type 3 concrete		Test 1 air content per 1/2 day of slip form paving to establish an air loss correction factor (ACF). See Special Provisions for additional information.
Slump		<b>For fixed form placement:</b> 1 per 300 yd <sup>3</sup> and as directed by the Engineer. Test first load each day per mix. <b>For slip form placement:</b> No slump testing required
Concrete Temperature		Record temperature each time air content, slump or strength test specimen is performed/fabricated by the Contractor.
Flexural Strength		1 beam (28 day) per day. Make additional control beams as necessary. Control beams shall be made within the last hour of concrete poured each day. Fabricate beams, deliver beams to curing site, and clean beam boxes. Cylinders may be substituted for beams at the discretion of the Engineer.
Concrete Pavement Texture		1 per 1000 lineal feet per lane of concrete pavement at locations determined by the Agency. All adjoining lanes shall be tested at the same location if paved at the same time. The Contractor supplies all materials necessary to perform the required testing.
Thickness		The Contractor drills concrete cores at locations determined by the Agency. The Contractor probes the plastic concrete at locations determined by the Agency.
Surface Smoothness		Contractor provides MnDOT certified inertial profiler results for the entire project as required by the contract. Check for current certification.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.



## 2404 CONCRETE WEARING COURSE FOR BRIDGES

Test Type (concrete manual)	Spec.	Contractor Testing	Agency Testing	<a href="#">Form</a>
Gradation, Quality, Coarse Agg -200 QC/Verification (5-694.145) (5-694.146) (5-694.148)	3126 3137	Prior to production, provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. No quality test results are required. Test Agency companion samples are Contractor's discretion.	1 per fraction prior to production and each time aggregate is delivered to the site.	2410 Sample ID Card
Air Content - Type 3 Concrete (Verification) (5-694.541)	<a href="#">Review Concrete Manual Website</a>	None	1 per 15 yd <sup>3</sup> , Test at beginning of pour each day.	Weekly Report of Low Slump Concrete
Slump (Verification) (5-694.531)		None	1 per 15 yd <sup>3</sup> , Test at beginning of pour each day. Allow mix to hydrate 5 minutes before slump test to assure all cement is saturated.	
Compressive Strength (5-694.511)		None	1 cylinder (28 day) per 30 yd <sup>3</sup>	2409 Cyl. ID Card

Test	Minimum Sample Size *companion req'd, double sample size	
Gradation	6 lb. for # 7	1.1 lb. Sand
Quality	50 lb. for Coarse Aggregate	30 lb. Fine Aggregate

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

**CONCRETE PAVEMENT REPAIR - CPR for 3U18**

Test Type	Spec.	Contractor Testing	Agency Testing	<a href="#">Forms</a>
Gradation, Quality, Coarse Agg -200	3126 3137	Prior to production, the Contractor shall provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. No quality test results are required. Test companion samples at Contractor's discretion.	Gradation: 1 per aggregate fraction prior to production and each time aggregate is delivered to the site. Quality Testing & Coarse Agg - 200: 1 test per aggregate fraction per source. The Agency may use the gradation results for the Quality Samples as a substitute for 1 required field gradation.	2410 Sample ID Card
Air Content - Type 3 Concrete	<a href="#">Review Concrete Manual Website</a>	None	1 per 15 yd <sup>3</sup> , Test at beginning of pour each day.	21412 Weekly Report of Low Slump Concrete
Slump		None	1 per 15 yd <sup>3</sup> , Test at beginning of pour each day. Allow mix to hydrate 5 minutes before slump test to assure all cement is saturated.	
Compressive Strength		None	1 cylinder (28 day) per 30 yd <sup>3</sup>	2409 Cyl. ID Card

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

## DOWEL BAR RETROFIT - DBR

Test Type	Spec.	Contractor Testing	Agency Testing	Form
Gradation, Quality, Coarse Agg -200	3126 3137	Prior to production, the Contractor shall provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. No quality test results are required. Test companion samples are Contractor's discretion.	1 per fraction prior to production and each time aggregate is delivered to the site.	2410 Sample ID Card

Test Type	Spec.	Agency Testing		Form
DBR Material Compressive Strength	<a href="#">Review Concrete Manual</a>	<b>Contractor Testing: None</b>		2409 Cylinder ID Card
		<b>Agency Testing:</b> During the pre-production test operations: 1 set of 3 cylinders tested at a rate as directed by the Engineer. Testing may need to be repeated if any problems with the dowel bar retrofit material are encountered. <b>First day of production:</b> 1 set of 3 cylinders at a rate directed by the Concrete Engineer. <b>After the first day of production:</b> 1 cylinder per day during production tested at a rate determined by the Engineer to determine traffic strength.		

Test	Minimum Sample Size *companion req'd, double sample size	
Gradation	1.1 lb. for # 89 & Sand	
Quality	50 lb. Coarse Aggregate	30 lb. Fine Aggregate

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

## LANDSCAPING AND EROSION CONTROL ITEMS

Kind of Material	Spec. #	Min. Required Acceptance Testing (Field Testing Rate)
Manufactured Topsoil Borrow, Salvaged Topsoil (stockpiled)	3877.2	As directed by the Engineer
Plant Stock & Landscape Materials	3861 and 2571.2A1	Materials must be in accordance with the Inspection and Contract Administration Guidelines for MnDOT Landscape Projects of which determines the minimum and maximum criteria thresholds. Certificate of Compliance, Nursery stock certificate registered with Mn Dept. of Agriculture. Out of state products subject to pest quarantines must be accompanied by documentation certifying all products are free of regulated pests.
Erosion Control Blanket	3885	Visual Inspection and Check approved products or approved vendors list - As directed by the Engineer.
Erosion Control Netting	3885	
Silt Fence	3886	
Erosion Stabilization Mat	3885	
Flotation Silt Curtain	3887	Accepted, based on manufacturers certification of compliance. Check weight of fabric.
Filter Logs	3897	Visual Inspection
Flocculants	3898	Obtain copy of Certificate of Compliance and MSDS
Fertilizer	3881	Obtain copy of invoice of blended material stating analysis.
Agricultural Lime	3879	Contractor must supply amount of ENP (Equivalent Neutralizing Power) for each shipment.
Mulch - Type 3	3882	Certified Weed Free (Certified sources only) Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA).
Mulch - Type 6 - Woodchips		All wood chips supplied by a supplier outside the Emerald Ash Borer quarantine area or have an Emerald Ash Borer Compliance Agreement with the MDA
Seeds	3876	(Certified Vendors Only) (Mixes 100-299) Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA).
Native Seed		(Mixes 300-399) certified seed only. Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA).
Sod	3878	Visual Inspection - Check approved products list - As directed by the Engineer. Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA) for salt tolerant sod.
Compost (from Certified Source)	3890	
Compost (from Non- Certified Source)		
Hydraulic Soil Stabilizer	3884	Check Approved/Qualified Products List - As directed by the Engineer.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

## CHEMICAL ITEMS

Kind of Material	Spec. No.	Min. Required Acceptance Testing (Field Testing Rate)
Asphalt Plank	3204	Visual Inspection - As directed by the Engineer.
Calcium Chloride	3911	Review the percentage required as per specification. Check for listing on Qualified Products website.
Magnesium Chloride	3912	
Hot-Pour Crack Sealant (for Crack Sealing/Filling)	3719 3723 3725	Retain Certification of Compliance. Check for listing on Qualified Products website.
Pavement Joint Adhesive	Special Provisions	Retain Certification of Compliance
<b>Waterproofing Materials</b>		
<a href="#">Membrane Waterproofing System</a>	3757	Visual Inspection - Check qualified products list.
<b>Waterproofing Materials - Three Ply System</b>		
Asphalt Primer	3165	Verify supplied material meets ASTM D 41
Waterproofing Asphalt	3166	Verify supplied material meets ASTM D 449
Fabric	3201	Verify supplied material meets ASTM D 41
<b>Paints</b>		
<a href="#">Waterborne Latex - Traffic Paint</a>	3591	Visual Inspection - Check qualified products list - retain Certificate of Compliance.
<a href="#">Epoxy Traffic Paint</a>	3590	
<a href="#">Traffic Marking Paint</a>	Special Provisions	
<a href="#">Non-Traffic Striping Paints</a>	3500 Series	Retain Certification of Compliance
<a href="#">Bridge Structural Steel Paint</a>	3520	Visual Inspection - Check approved products list - retain Certificate of Compliance.
<a href="#">Exterior Masonry Paint</a>	3584	
<a href="#">Noise Wall Stain</a>	Special Provisions	
<a href="#">Drop-on Glass Beads</a>	3592	Visual Inspection - Check qualified products list. Retain Certificate of Compliance.
<a href="#">Pavement Marking Tape</a>	3354	Visual Inspection - Check qualified products list. Retain Certificate of Compliance.
	3355	
	Special Provisions	
<a href="#">Signs and Markers</a>	3352	Visual Inspection - Check qualified products list.

**Metals 1 of 2**

<b>Kind of Material</b>	<b>Spec. No.</b>	<b>Min. Required Acceptance Testing (Field Testing Rate)*</b>
<b>Guard Rail</b>		
Fittings - Splicers, Bolts, Posts etc.	3381	Visual Inspection - Materials shall be approved before use. Call MnDOT inspector at 218-846-3613 to see if material has been approved.
Structural Plate Beam	3382	
Non-High Tension Guard Rail Cable	3381	
High Tension Guard Rail Cable	Special Provisions	
<b>Steel Posts</b>		
Steel Sign Posts	3401	Visual Inspection - As directed by the Engineer. Retain Certificate of Compliance in Project file.
Fence Posts, Brace Bars, Rails and others	3403	Visual Inspection - As directed by the Engineer. Retain Certificate of Compliance and certified mill analysis in project file.
	3406	
	3379	
<b>Fence</b>		
Barbed Wire	3376	Visual Inspection Retain Certification of Compliance, As directed by the Engineer.
Woven Wire		
Chain Link Fabric		
Components: cup, cap, nut, bolt, end clamp, tension band, truss rod tightener, hog ring, tie wire, tension stretcher bar, truss rod, clamp & tension wire		
Gates		
<b>Pipe</b>		
Water Pipe and other Piping Materials	3364, 3365, 3366 & Special Provisions	Visual Inspection - As directed by the Engineer.
<b>Reinforcing Steel - Inspected by MnDOT &amp; will be charged back to the Local Agency.</b>		
Uncoated Bars	3301	Retain Certificate of Compliance & Certified Mill Analysis
Epoxy Coated Bars	3301	For Epoxy-Coated bars, steel will be tagged "Inspected" when it has been sampled and tested by Mn/DOT prior to shipment, & it will be tagged "Sampled" when testing has not been completed prior to shipment. If the Epoxy-Coated bars are not tagged "Sampled" or "Inspected", submit samples (1 bar 3ft long for each size for each day's coating production), Certificate of Compliance, & Certified Mill Analysis for testing. Maintain original Cert. of Compliance & Certified Mill Analysis in project file.
Spirals	3305	
Stainless Steel Bars	Special Provisions	Visual Inspection Testing as directed by the Engineer (2 bars 3 ft. long per heat per bar size). Certified Mill Test Reports to be filed.

## Metals 2 of 2

Kind of Material	Spec. No.	Min. Required Acceptance Testing (Field Testing Rate)*
<b>Reinforcing Steel - Inspected by MnDOT &amp; will be charged back to the Local Agency.</b>		
Steel Fabric	3303	2 sq ft if epoxy coated.
Dowel Bars	3302	One dowel bar and basket from each shipment.
Prestress/Post Tension Strands	3348 Spec.Prov.	One sample of 2 strands by 6 ft from each heat/production lot.
<b>Castings</b>		
<u>Drainage Castings</u>	3321	Visual Inspection - Check approved / qualified list.
	2471	
<u>Electrical</u>	2565	
Anchor Rods (Cast in Place) and Structural Fasteners	3385 3391	Visual Inspection - Check approved / qualified list. Testing as directed by the Engineer, (see Notes below)
<p>Notes: Manufacturer must have one yearly passing test from the Department for each anchor rod or bolt type. Prior to installation, obtain copy of Mn/DOT passing test report from supplier. Specs 3385.2 A, B, &amp; C require anchor rod markings per ASTM F 1554 S3. The end of each anchor bolt intended to project from the concrete must be die stamped with the grade identification as follows: Grade 36 = AB36, Grade 55 = AB55, Grade 105 = AB105.</p>		
<u>Anchorage (Drilled In)</u>	Special Provisions	Visual Inspection - Check qualified products list.
<b>Structural Steel - Inspected by MnDOT &amp; will be charged back to the Local Agency.</b>		
Steel Bridge - Beams, Girders, Diaphragms, etc.	2471	Structural Metals Inspection Tag and field inspection for damage/defects, check dimensions for contract compliance. Review approved products list as directed by the Engineer.  Note: Structural metals products will be inspected at the plant and will be shipped with a Structural Metals Inspection Tag. An inspection confirmation report will be completed by Structural Metals Inspection staff and sent to the field personnel. Only approved suppliers are allowed to supply Structural Metals products. A list of approved suppliers can be found on the Bridge Office web site: <a href="http://www.dot.state.mn.us/bridge/">http://www.dot.state.mn.us/bridge/</a>
Concrete Girders-Diaphragms and sole plates		
Expansion Joints		
Steel Bearings		
Railing-Structural tube and ornamental		
Drainage Systems		
Protection Angles		
Overhead Sign structures	2564 2471	
High Mast Lighting Structures	2545 2471	
Monotube Signal Structures	2565 2471	

\* Check domestic steel requirement under 1601 Special Provision.

## Geosynthetics, Pipe, Tile, Precast/Prestressed Concrete

Kind of Material	Spec. No.	Min. Required Acceptance Testing (Field Testing Rate)
<b>Corrugated Metal Products</b>		
Culvert Pipe Under drains Erosion control Structures	3225 thru 3229, 3351, 3399	Make certain pipe is Certified on Invoice, retain certificate of compliance and certified mill analysis in project file.
Structural Plate	3231	
Aluminum Structural Plate	3233	Retain the Certificate of Compliance and certified mill analysis in project file.
<b>Pipe</b>		
Clay Pipe	3251	Visual Inspection
Reinforced Concrete Pipe and Arches, Precast Cattle Pass Units, Sectional Manhole Units	3236	Field Inspection: Check for damage and defects. Check dimensions and class as required.
Non-Reinforced Concrete Pipe	3253	
Drain Tile (Clay or Concrete)	3276	Visual Inspection - Acceptance as directed by the Engineer.
Thermoplastic (TP) Pipe ABS and PVC	3245	Obtain Certificate of compliance. Check for approved marking printed on pipe. Field Inspect for damage or defects.
Corrugated Polyethylene Pipe	3278	Check for markings (AASHTO M 252) Certificate of Compliance. Field Inspect for damage or defects.
<a href="#">Corrugated Polyethylene Pipe - Dual Wall 12"-48"</a>	3247	Visual Inspection - Check approved products list. Obtain Certificate of Compliance.
<b>Precast/Prestressed Concrete Structures - Inspected by MnDOT &amp; will be charged back to the Local Agency.</b>		
Reinforced Precast Box Culvert	3238	Field Inspection: Check for damage and defects. Check dimensions as required. Check for the "MnDOT" stamp and signature on the certification document.
Precast/Prestressed Concrete Structure (beams, posts, etc.)	2405	
Manholes and Catch Basins (Construction)	2506 3622	
Sewer Joint Sealing Compound	3724	Visual Inspection - Acceptance as directed by the Engineer.
Preformed Plastic Sealer for Pipe	3726 Type b	Visual Inspection - Acceptance as directed by the Engineer.
Bituminous Mastic Joint Sealer for Pipe	3728	
EPS Geofoam	Special Provisions	Visual Inspection - Acceptance as directed by the Engineer. Check for yellow aged material, uniformity and dimensions.
Geotextile Fabric and Geogrid Reinforcement	3733 and Special Provisions	Obtain Certificate of Compliance stating minimum average roll values (MARV). MARV must meet Project requirements. Fabric must be listed on Geotextile Small Quantity Acceptance List available at <a href="http://www.dot.state.mn.us/materials/aggregatedocs/gtxlist.pdf">http://www.dot.state.mn.us/materials/aggregatedocs/gtxlist.pdf</a>
<a href="#">Geotextile Small Quantity Acceptance List</a>		
<a href="#">Silt Fence</a>	3886	Visual Inspection - Check approved products list.



**ELECTRICAL AND SIGNAL EQUIPMENT ITEMS 1 of 2**

<b>Kind of Material</b>	<b>Spec. No.</b>	<b>Min. Required Acceptance Testing (Field Testing Rate)</b>
Lighting Standards (Aluminum or Steel)	3811	Visual Inspection - Obtain Certificate of Compliance. The Fabricator will submit "Certificate of Compliance", on a per project basis, to the Project Engineer.
<u>Hand Holes (Precast, PVC, and LLDPE)</u>	2545	Visual Inspection - Check approved/qualified products list. Traffic signal and street lighting projects require hand holes to be listed on the Mn/DOT Signals Approved Products List (APL). For cast iron frame and cover: see Metals - Drainage and Electrical Castings
	2550	
	2565	
Foundation	2545	Slump as needed, 1 cylinder per 25 cu.yds. Rebar is required in concrete foundations as specified in the Contract documents for all traffic control signals and roadway lighting projects.
Steel Screw In Foundations	2545 2565	See Approved/Qualified Products List for Roadway Lighting and Signals.
<b>Conduit and Fittings</b>		
Metallic	3801	Visual Inspection - Conduit shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL). For traffic signal and street lighting projects, specific requirements are contained in the Special Provisions for each project.
	3802	
Non-Metallic (Rigid and HDPE)	3803	
	Special Provisions	
Anchor Rods and Bolts (Cast in Place)	3385	Visual Inspection - Manufacturer must have one yearly passing test from the Department for each anchor rod or bolt type. Prior to installation, obtain copy of Mn/DOT passing test report from supplier. Specs 3385.2 A, B, & C require anchor rod markings per ASTM F 1554 S3. The end of each anchor bolt intended to project from the concrete must be die stamped with the grade identification as follows: Grade 36 = AB36, Grade 55 = AB55, Grade 105 = AB105.
<u>Anchorage (Drilled In)</u>	Special Provision	Visual Inspection - Check qualified products list.
<u>Miscellaneous Hardware</u>	2545 2565	Visual Inspection - Check approved products list. Will carry "Inspected" tag if sampled and tested prior to shipment. No sample necessary if "Inspected". Do not use if not tested. Field sample at sampling rate for laboratory testing. For traffic signal and street light lighting projects, various miscellaneous hardware is required to be listed on the Mn/DOT Signals and Lighting Approved Products Lists (APL). The Contract documents indicate, which items must be on the Signals and/or Lighting APL.
<b>Cable and Conductors</b>		
Power Conductors	3815.2B1	Visual Inspection - Make certain the conductors are the type specified. Submit Field Inspection report showing type and quantities used. Shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL) and type where applicable.
Loop Detector Conductors (No Tubing)	3815.2B2 (a)	

**ELECTRICAL AND SIGNAL EQUIPMENT ITEMS 2 of 2**

<b>Kind of Material</b>	<b>Spec. No.</b>	<b>Min. Required Acceptance Testing (Field Testing Rate)</b>
Electrical Cables and Single Conductors with Jacket	3815.2B2(b) 3815.2B3	Visual Inspection - Usually inspected at the distributor. Documentation showing project number, reel number(s), & Mn/DOT test number(s) will be included with each project shipment. If such documentation is not received from Contractor, submit sample for testing along with material certification from manufacturer. Do not use if not tested. Pre-inspected materials will not be tagged; an inspection report will be sent by the Mn/DOT inspector for each shipment. Project inspectors should verify that the shipping documents agree with this inspection report. Call Steve Grover at 651-366-5540 or Cindy Schellack at 651-366-5543 with questions. For traffic signal and street lighting projects, the Special Provisions for each project contain electrical cable and conductor specifications.
	3815.2B5	
	3815.2C1 thru .2C8	
	3815.2C14	
	Special Provisions	
Fiber Optic Cables	3815.2C13	Visual Inspection - Check approved products list for Traffic Management Systems.
Ground Rods	2545	Visual Inspection - Check approved products list. Shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL). Detail materials on Materials Acceptance Summary.
	2565	
Luminaires and Lamps	3810	Visual Inspection - Check approved products list. Traffic signal and street lighting projects require luminaires and lamps to be listed on the Mn/DOT Lighting Approved/Qualified Products List (APL). The conductors shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL) and type, where applicable.
Electrical Systems	2565	Electrical Systems are to be reported as a "System" using the LIGHTING, SIGNAL AND TRAFFIC RECORDER INSPECTION REPORT. To be certified by the Project Engineer.
Traffic Signal Systems	2565	Traffic Signal Systems are to be reported as a "System" using the LIGHTING, SIGNAL AND TRAFFIC RECORDER INSPECTION REPORT. To be certified by the Project Engineer.

## Brick, Stone and Masonry Units

Kind of Material	Spec. No.	Min. Required Acceptance Testing (Field Testing Rate)
<b>Brick</b>		
Sewer (clay) and Building	3612 to 3615	Visual Inspection - Acceptance as directed by the Engineer.
Sewer (Concrete)	3616	Visual Inspection - Acceptance as directed by the Engineer. Air entrainment required. Obtain air content statement from supplier.
<b>Concrete Masonry Units</b>		
Sewer Construction	3621	Visual Inspection - Acceptance as directed by the Engineer. Air entrainment required. Obtain air content statement from supplier.
<a href="#"><u>Modular Block Retaining Walls</u></a>	Review Current Special Provisions	Visual Inspection - Note: All lots of block upon delivery shall have Manufacturer or Independent laboratory test results to verify passing both compression and freeze-thaw requirements. * Wall units and cap units are considered separate block types.
Reinforced Concrete Cribbing	3661	Visual Inspection - Acceptance as directed by the Engineer. Will be stamped when inspected prior to shipment.
Stone for Masonry or Rip-Rap	3601 and Special Provisions	Visual Inspection - Acceptance as directed by the Engineer.
REMARKS: Each source shall be approved by Project Engineer or Supervisor for quality, prior to use. For questions on quality, contact District Materials or Geology Unit.		

## Miscellaneous Materials

Kind of Material	Spec. No.	Min. Required Acceptance Testing (Field Testing Rate)
Timber, Lumber Piling & Posts	3412 to 3471 & 3491	Visual Inspection - Acceptance as directed by the Engineer. Untreated materials shall be inspected in the field. Treated materials shall be Certified on the Invoice or Shipping Ticket. Material is inspected and stamped by an Independent Agency as per Specification 3491. Contact Laboratory for additional information.
Miscellaneous pieces and Hardware (Galvanized)	3392 3394	Visual Inspection - Acceptance as directed by the Engineer.
Insulation Board	3760	
<a href="#">Elastomeric Bearing Pads - Plain or Laminated</a>	3741 and Special Provisions	Check dimensions. Check repair of tested pad. Obtain copy of Certificate of Compliance. <b>DO NOT USE ANY PADS THAT ARE NOT CERTIFIED.</b>
Cotton Duck Bearing Pads		

## Approved/Qualified Products

[Asphalt Products](#)

[Roadside Safety Hardware](#)

[Bridge Products](#)

[Roadway Lighting Products](#)

[Concrete Products](#)

[Traffic Control Signals Products](#)

[Crack & Joint Materials Products](#)

[Signing Products](#)

[Truncated Domes](#)

[Snow and Ice Chemical Products](#)

[Drainage](#)

[Temporary Traffic Control Devices](#)

[Erosion Control and Landscaping Products](#)

[Traffic Management Systems/ITS](#)

[Geosynthetics](#)

[Vehicle Safety Lighting](#)

[Maintenance Shop Supplies](#)

[Walls \(Retaining/Noise\)](#)

[Paint/Stain/Coating Systems \(Non-Pavement\) Products](#)

### SALT Construction Website - Additional Resources

[Bituminous Engineering](#)

[Asphalt Binder Certified Supplier](#)

[Asphalt Emulsion Certified Supplier](#)

[Concrete Engineering](#)

[MnDOT Concrete Manual](#)

[QC & QA RM Plant Workbooks](#)

[MnDOT Certified Ready-Mix Program](#)

[Grading & Base Engineering](#)

[Testing procedures in the Grading & Base Manual.](#)

[Forms and worksheets at the Grading & Base Website.](#)

[Gradation worksheets at the SALT Construction Website](#)

## **SALT SMC - LGA Contacts**

### **Districts 1, 2, 3, 4**

Ron Bumann - State Aid Construction Practices Specialist

[ronald.bumann@state.mn.us](mailto:ronald.bumann@state.mn.us)

218-725-2811

### **Districts 6, 7, 8**

Mitch Bartelt - State Aid Construction Engineer

[mitch.bartelt@state.mn.us](mailto:mitch.bartelt@state.mn.us)

651-366-3832

### **Metro**

Elisa Bottos - State Aid Construction Engineer

[elisa.bottos@state.mn.us](mailto:elisa.bottos@state.mn.us)

651-234-7766

Jim Deeny - State Aid Construction Liaison

[james.deeny@state.mn.us](mailto:james.deeny@state.mn.us)

651-234-7762

## Telephone Index for MnDOT Specialty Offices

### Grading & Base

Terry Beaudry	(651) 366-5456
John Bormann	(651) 366-5496
Melissa Cole	(651) 366-5432

[Website: www.dot.state.mn.us/materials/gradingandbase.html](http://www.dot.state.mn.us/materials/gradingandbase.html)

### Bituminous

John Garrity	(651) 366-5577
Asphalt Binder	
Jim McGraw	(651) 366-5548
Jason Szondy	(651) 366-5549

### Bituminous Specialty Items

Terry Beaudry	(651) 366-5456
Greg Schneider	(651) 366-5403
Melissa Cole	(651) 366-5432
Tom Wood	(651) 366-5573

[Website: www.dot.state.mn.us/materials/bituminous.html](http://www.dot.state.mn.us/materials/bituminous.html)

### Concrete

Concrete – Aggregates and Mix Design	
Concrete – Certified Ready Mix Concrete	
Wendy Garr	(651) 366-5423
Concrete – Paving	(651) 366-5576
Rob Golish	
Concrete – Bridges	(651) 366-5575
Ron Mulvaney	
Concrete – Pavement Rehabilitation	
Gordy Bruhn	(651) 366-5523

[Website: www.dot.state.mn.us/materials/concrete.html](http://www.dot.state.mn.us/materials/concrete.html)

### Landscaping and Erosion Control Items

Erosion Control	(651) 366-3607
Lori Belz	
Landscaping	(651) 366-4612
Scott Bradley	
Wood Chips	(651) 366-3619
Tina Markeson	

### **Chemical Items**

Allen Gallistell	(651) 366-5545
Dave Iverson	(651) 366-5550

### **Metallic Materials and Metal Products Sampling**

Steve Grover	(651) 366-5540
Laboratory - Test Results	(651) 366-5560
Bridge Structural Metals	
Todd Niemann	(651) 366-4567
Barry Glassman	(651) 366-4568

### **Miscellaneous Materials**

Steve Grover	(651) 366-5540
Bearing Pads	
Todd Niemann	(651) 366-4567
Barry Glassman	(651) 366-4568
Laboratory - Test Results	(651) 366-5560

### **Geosynthetics, Pipe, Tile, and Precast/Prestressed Concrete**

Steve Grover	(651) 366-5540
Rich Lamb	(651) 366-5595
Randy Tilseth	(651) 366-5451
Laboratory - Test Results	(651) 366-5560

### **Brick, Stone and Masonry Units/Modular Retaining Wall Blocks**

Steve Grover	(651) 366-5540
Blake Nelson	(651) 366-5599
Laboratory - Test Results	(651) 366-5561

### **Electrical & Signal**

Susan Zarlring	(651) 234-7052
Steve Grover	(651) 366-5540
Wendy Garr - Concrete	(651) 366-5423
Laboratory - Test Results	(651) 366-5560



## Materials Lab. Contacts

## Independent Assurance

<p><b>District 1, Duluth</b> Leila DeLuca, Linda Pearson, 218-725-2738 Fax 218-725-2814</p>	<p>Nadine Miller (218) 725-2737 Cell (218) 348-6297</p>
<p><b>District 2, Bemidji</b> Jeff Long, 218-755-6544 Jason Kisseo, 218-755-6542 Fax 218-755-6540</p>	<p>Thomas Lloyd (218) 755-6545 Cell (218) 766-6949</p>
<p><b>District 3A, Baxter</b> Tom Boser, 218-828-5755 Fax 218-828-5816</p>	<p>- (218) 828-5753 Cell (218)232-6748</p>
<p><b>District 3B, Saint Cloud</b> Teresa Mertens, 320-223-6555 Fax 320-223-6582</p>	<p>Teresa Mertens, 320-223-6555 Cell (320) 493-3559</p>
<p><b>District 4, Detroit Lakes</b> Brad Hanson, 218-846-3616 Bruce Bryngelson, 218-846-3614 Wayne Koons, 218-846-3617 Fax 218-846-0744</p>	<p>David Brunner      Dist. 4 Mat'ls (218) 846-3613 Cell (218) 849-7393 Sandy Kay Wollschlager 4B Mat'ls (320) 589-7300 Cell (320) 815-6660</p>
<p><b>Metro District,</b> Maplewood Lab Mike Evans, 651-366-5409 Fax 651-366-5408</p>	<p>Waters Edge Mat'ls      (651) 234-7356 East Steve Reinardy      (651) 755-1581 Mike Sroga      (651) 775-0997 West Greg Bohmert      (651) 775-1005 Dave Wilkerling      (651) 775-1042</p>
<p><b>District 6, Rochester</b> Ken DeCramer, 507-286-7580 Ken Pickett, 507-286-7586 Brad Horn, 507-286-7535 Fax 507-285-7112</p>	<p>Brandon Weick      (507) 286-7584 Cell (507) 251-0138</p>
<p><b>District 7, Mankato</b> Mark Schoeb, 507-304-6186 Scott Swanson, 507-304-6189 Fax 507-304-6191</p>	<p>Mitch Jordahl      (507) 304-6187 Cell (507) 380-9619 Brian Lueck      (507) 304-6188 Cell (507) 380-8248</p>
<p><b>District 8A, Willmar</b> Jay Jorgensen, 320-214-6345 Fax 320-214-6306 <b>District 8B, Marshall</b> Mark DeAustin, 507-537-2068 Fax 507-537-3802</p>	<p>Jon Vlaminck      (320) 214-6348 Cell (320) 894-7409</p>

Lbs

Bituminous	35	Aggregate for Gradation QC/QA
	80	for each plus #4 Aggregate Type for Quality Testing
	35	for each minus #4 Aggregate Type for Quality Testing
	80	for each RAP material for Quality Testing
	10	RAS (shingles) for Processsed Gradation and Quality Testing
	65	for Mix Properties (QC/QA) 3 full 6" by 12" cylinder molds for QA
	90	for TSR (QC/QA) 4 full 6" by 12" cylinder molds for QA
	90	for Aggregate Specific Gravity QC/QA
	-	1 quart of Asphalt Binder QA
	-	1/2 gallon for Asphalt Emulsion QA
Grading & Base	30	Aggregate for Gradation (Companion sample from 60 lb split).
	25	Moisture Density Test - Proctor (Companion from 50 lb split).
	30	Aggregate Quality/Percent Crushing Test - 1 per source
Ready-Mix Concrete	25	Gradation 3/4" plus
	10	Gradation 3/4" minus
	6	Gradation CA 70 & #7
	1	Gradation - Sand (500 g), CA 80, #89.
	4.4	Moisture Test Coarse Aggregate (2000 g)
	1.1	Moisture Test Fine Aggregate (500 g)
	50	Quality 3/4" plus - lab sample
	30	Quality 3/4" minus - lab sample
	30	Fine Aggregate - lab sample
	10	3/4" Plus for the -200 Coarse Aggregate Test (5000 grams)
	6	3/4" Minus for the -200 Coarse Aggregate Test (2500 grams)
	5	Cement, Blended Cement, Fly Ash
	-	1/2 pint plastic container for admixtures.