

2018 SALT Schedule of Materials Control - Local Government Agency

This Schedule of Materials Control (SMC) outlines the minimum testing requirements for State Aid Funded and/or Federal Aid Projects off the National Highway and Trunk Highway System. Optional to this SMC is the MnDOT Materials Control Schedule. Usage of either schedule must be defined in the project proposal.

1603.2 SAMPLING AND TESTING - INSERT INTO SPECIAL PROVISIONS

The first paragraph is hereby deleted and replaced with the following:

Sampling and testing of materials for this project will be in accordance with the State Aid for Local Transportation (SALT) "Schedule of Materials Control – Local Government Agency" (SMC-LGA). The SMC-LGA establishes the size of samples and the minimum rate of testing. The SMC-LGA references the 2016 and 2018 MnDOT Standard Specifications for Construction and does not set contract requirements for the material.

The SMC - LGA serves as a guide for material testing with allowable acceptance "as directed by the Engineer" detailed in Specification 1501.1(1) - Authority of the Engineer. These testing rates are a minimum and additional tests may be taken at the Engineer's discretion. A minimal testing rate does not always ensure a quality product; field observations and attention to detail is crucial. Materials not listed on an approved products list may be sampled and tested as directed by the Engineer. Materials listed on a Qualified Products list may be accepted or tested at the discretion of the Engineer.

Federal Aid projects require Independent Assurance Inspection. Contact the MnDOT District IA Inspector when the job starts to provide the proper servicing of your project.

Definitions

[SALT Construction Website](#)

MnDOT Office of State Aid for Local Transportation. The SMC - LGA is located at the construction page under "Information & Resources - Materials".

[MnDOT Schedule of Materials Control](#)

Schedule of Materials Control (SMC) are inserted into project proposals to direct how materials are to be sampled. The SMC is updated yearly. Each SMC is project specific. Therefore, one needs to refer to their specific proposal.

[Approved Products List](#)

Products are "approved" when they have been found to routinely meet all applicable standards and specifications. The product is placed on the list based upon established successful manufacturer's quality control and warranties, but the listing may expire or require periodic renewal to verify the product has not changed over time. The approval process for the individual product should specify any expiration requirement.

[Qualified Products List](#)

Products are predicted to meet all applicable standards and specifications, but random sample testing is required to verify specific product lots meet specifications prior to usage. These products are generally considered to be "qualified" but not approved until tested for compliance. Successfully tested products lots are considered to be "approved". The approval process for the individual product should specify any further testing requirements for the product.

[Certified Sources](#)

Certified Sources must comply with each individual product's defined "certification procedure". Acceptance of products from certified sources follows the same sampling and testing as "qualified" products.

Quality control (QC) :The activities performed by the **Contractor/Producer** that have to do with making sure the quality of a product or process meets the relevant contract requirements.

Quality assurance (QA) : The activities performed by the **Department/Agency** that have to do with making sure the quality of a product or process meets the relevant contract requirements.

Verification Testing: Sampling and testing performed by the **Department/Agency** to validate the quality of the product per Title 23-Highways, Code of Federal Regulation 637.203. **Part of QA.**

Material Acceptance Summary

LOCAL NO. _____
 SAP/SP NO. _____

| Bid Item # | Item Description | Qualified Product List | Approved Product List | Certificate of Compliance | Accepted by Engineer* |
|------------|--------------------------------------|------------------------|-----------------------|---------------------------|-----------------------|
| 2105.604 | Geotextile Fabric Type VI-A | | | | |
| 2105.604 | Soil Stabilized Geogrid | | | | |
| 2357.606 | Bituminous Tack Coat | | | | |
| 2357.606 | Bituminous Tack Coat Shoulder | | | | |
| 2511.504 | Geotextile Filter Type IV | | | | |
| 2433.607 | Cement Grout | | | | |
| 2411.604 | Modular Block Retaining Wall | | | | |
| 2573.502 | Silt Fence - MS | | | | |
| 2573.505 | Floatation Silt Curtain, still water | | | | |
| 2573.505 | Sediment Control Log - wood fiber | | | | |
| 2574.508 | Fertilizer type 3 & 4 | | | | |
| 2575.502 | Seed Mixtures | | | | |
| 2575.523 | Erosion Control Blankets CAT 3 | | | | |
| 2575.560 | Hydraulic Bonded Fiber Matrix | | | | |
| 2575.571 | Rapid Stabilization Method 3 | | | | |
| 2580.603 | Interim Pavement Marking | | | | |
| 2582.603 | Pavement Marking Special | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |
| | | | | | |

* Items not included on the Approved Product List or the Manufacturer's Certifications have not been received are hereby accepted by the Engineer. Materials on a Qualified Products list which have not been tested at the discretion of the Engineer are hereby accepted.

signed: _____
 Project Engineer Date

BITUMINOUS QUALITY MANAGEMENT

The Contractor shall provide and maintain a quality control program as detailed in Specification 2360.2.G.
The Engineer shall review the quality control program for compliance.

| | Type of Test | Spec Section (1) | Contractor / Producer - QC Testing Rates | Agency - QA Testing Rates | |
|---------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------|---------------------------|---------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------|--|
| Start-Up Testing Rates for the 1st 2000 tons (2) | Bulk Specific Gravity | 2360.2.G.7.b | 1 test per 500 tons 55 lb. sample 3 full cylinder molds | (3) 1 Verification Mixture Sample test per day, all Verification samples are from a split (QC/QA) sample. | |
| | Maximum Specific Gravity | 2360.2.G.7.c | | | |
| | Air Voids (calculated) | 2360.2.G.7.d | | | |
| | Asphalt Content | 2360.2.G.7.a | | | |
| | Adj. Asphalt Film Thickness (AFT) | 2360.2.E.7.e | | | |
| | Gradation | 2360.2.G.7.f | | | |
| | Fines to Effective Asphalt Ratio calc'd | 2360.2.G.7.a/f | 1 test per 1000 tons (4) (5) (6) | | |
| | Coarse Aggregate Angularity (CAA) | 2360.2.G.7.g | | | |
| | Fine Aggregate Angularity (FAA) | 2360.2.G.7.h | | | |
| Added AC/Total AC Ratio (calc'd) | 2360.2.G.7.a | | | | |
| Production Testing Rates | Bulk Specific Gravity | 2360.2.G.7.b | 1 test per 1000 tons 55 lb. sample 3 full cylinder molds | (3) 1 Verification Mixture Sample test per day/ mix type, submit companion to the QC - CAA & FAA test results. | |
| | Maximum Specific Gravity | 2360.2.G.7.c | | | |
| | Air Voids (calculated) | 2360.2.G.7.d | | | |
| | Asphalt Content | 2360.2.G.7.a | | | |
| | Adj. Asphalt Film Thickness (AFT) | 2360.2.E.7.e | | | |
| | Gradation (minimum of 1 per day) | 2360.2.G.7.f | | | |
| | Added AC/Total AC Ratio (calculated) | 2360.2.G.7.a | | | |
| | Coarse Aggregate Angularity (CAA) | 2360.2.G.7.g | (4) (5) | | |
| | Fine Aggregate Angularity (FAA) | 2360.2.G.7.h | (4) (6) | | |
| | TSR | 2360.2.G.7.i | When directed by the Materials Engineer | | |
| | Aggregate Specific Gravity | 2360.2.G.7.j | As directed by the Engineer | | |
| | Mixture Moisture Content | 2360.2.G.7.k | | | |
| | Asphalt Binder Certified Supplier | 2360.2.G.7.l | (7) (1qt. Steel container for asphalt binder. 1/2 gal. plastic container with wide screw top for emulsion) | | |
| | Asphalt Emulsion Certified Supplier | 2357 | | | |
| Compaction / Density Requirements | 2360.3.D | Review special provisions | | | |
| Small Quantity Requirements | < 300 tons per day. See 2360.2G.5 & 2360.3G | | | | |
| Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of materials Control Rates and will be billed accordingly. | | | | | |

NOTES Testing rates are minimums, additional testing is encouraged to ensure a quality product.

- (1) Review Special Provisions & 2360.2.G Mixture Quality Management.
- (2) The testing rates apply only to mixtures that have not been tested on previous projects in the current year.
- (3) Companion Sample should be collected from each QC sample. Submit one per day for Verification Testing.
- (4) The Contractor will retain the extracted gradation samples in containers with field identification numbers for a period of 10 calendar days. The Engineer will identify which extracted gradation sample is the Verification Companion Sample and whether it is to be tested for coarse and fine aggregate angularity.
- (5) **At start-up or new Mix Design:** 2 tests per day for a minimum of 2 days, then 1/day if CAA is met. If CAA > 8% of requirement, 1 sample per day but test 1/ week. No testing reqd for Class A and B Aggregates.
- (6) **At start-up or new Mix Design:** 2 tests per day for a minimum of 2 days, then 1/day if FAA is met. If FAA > 5% of requirement, 1 sample per day but test 1/week.
- (7) Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer

BITUMINOUS SPECIALTY ITEMS

| Type of Test | Spec | Contractor/Producer - QC Testing Rates | Agency- QA Testing Rates |
|------------------------------------------------------------------------------------------------------------------------------------------|-----------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Gradation | 2363 | 1 per 1,000 Ton with a minimum 1 per day. | 1 per day. 35 lbs. |
| PASSRC & PASB | 3139.3 | | |
| Micro-Surfacing | 2354 3139.5 | Stockpile: 1/1,500 Tons (min 1/day) Machine Hopper: 1/500 Ton (min 1/day) | Stockpile & Machine Hopper: 1/day 30 lbs. |
| Seal Coat, Underseal & Otta Seal | 2356 3137.2B | Stockpile: 1/1,500 Tons (min 1/day) Chip Spreader Hopper: 1/day | 1/day from Hopper. 30 lbs. |
| % Crushing - CAA | 2363 | 1 per 1,000 Ton with a minimum 1 per day. | 1 per day from gradation test. 35 lbs. |
| PASSRC & PASB | 3139.3 | | |
| Moisture / Aggregate | 2354 | Machine Hopper: 1/500 Tons (min 3/day) | 1/day 2lbs |
| Micro-Surfacing | 3139.5 | | |
| Sand Equivalence | 2354 | 1/day | test at Engineer discretion, 25 lbs. |
| Micro-Surfacing | | | |
| Flakiness Index | 2356 | Sample taken from first load on first day, submit to Agency: 30 lbs. | Agency will test at their discretion, see Lab Manual 1223 |
| Bituminous Seal Coat & Bituminous Underseal | | | |
| Bituminous Mixture | 2353 | 1/300 Tons, min 1/day. %AC, Gradation, Max SpG, Adj.AFT | 1/day, 20 lbs. 1 cylinder from truck box. |
| UTBWC | 3151.2G | | |
| PASSRC & PASB | 3151 2363 | Asphalt spot check: min 1/day | - |
| Stone Matrix Asphalt - SMA Lab Manual 1203, 1204, 1205, 1211, 1214, 1806, 1807, 1808, 1813, 1853, 1854, 1855, AI SP-2 AASHTO T305 | 2365 | Tests , %AC, gradation, Gmm, Gmb, Voids, VMA, CAA, Draindown, VCA, fines/effective asphalt. Rate, (1/1000 tons, min. 1/day) Agg SpG, mix moisture, TSR to be tested as directed by Engineer. Submit companion 1 per day to agency: 3 full 6" by 12" cylinders | Tests: %AC, Gradation, Gmm, Gmb, Voids, VMA, CAA, VCA, fines/effective asphalt. Agency is not required to do draindown. Copy MDR to Project Engineer and Grading & Base Engineer. |
| Asphalt Binder Tests | | <u>Asphalt Emulsion List</u> | <u>Asphalt Binder List</u> |
| UTBWC | 2353 3151 | Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer : Asphalt Binder: First load, then 1/250,000 gallons. Sample size of 1 quart metal container. Emulsified Asphalt: First load, then 1/50,000 gallons. Sample size of 1/2 gallon wide screw top plastic container. | |
| Micro-Surfacing | 2354 | | |
| Seal Coat, Underseal & Otta Seal | 2356 | | |
| Tack Coat | 2357 | | |
| PASSRC & PASB | 3151 | | |
| Asphalt Binder Rate | 2354 | Verify Application Rate 3/day | Verify Application Rate 1/day |
| Micro-Surfacing | | | |
| Fog Seal | 2355 | Verify Application Rate 1/day | Verify Application Rate 1/day |
| Seal Coat, Underseal & Otta Seal | 2356 | | |
| Bit Tack Coat | 2357 | | |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

Cold Inplace Recycling (CIR) & Stabilized Full Depth Reclamation (SFDR)

Specification 2215

| Test Type | Contractor/Producer QC Testing Rates | Agency QA Testing Rates | Grading & Base Manual/Form |
|-----------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------|
| Gradation SFDR (Simple) Pre-ground un-stabilized material | 1 per mile - report sieves 2" & 3" | Run gradation at the discretion of the Engineer | .215 / 101 report sieve 2" & 3" |
| Gradation (Entire) (Material to be stabilized) | One per day, give split sample to the Engineer | Run gradation at the discretion of the Engineer | .215 / 101 report sieve 2", 1.5", 1.25", 1", 3/4", 3/8", #4, #10, #30. |
| Gradation (Simple) (Material to be stabilized) | 1 per mile for SFDR & CIR w/o top size screening. 4 / mile for CIR with top size screens. | Run gradation at the discretion of the Engineer | .215 & .293 / 101 report sieve 2" & 1.5" for SFDR, 1.5" and 1.25" for CIR |
| Depth Check - Unstabilized and Stabilized | 1 per 1,000' /machine width for each vertical machine face for initial pulverization and stabilization. | 1 per day | .284 / 401 |
| SFDR: Moisture during compaction of unstabilized portion | 1/6,000 sq. yd.tolerance on optimum moisture from target? | none | .245 Speedy tester not allowed. |
| Penetration Index (DCP) - SFDR only Unstabilized. | 1 per 1/2 mile lane mile | 1 per lane mile | .255 / 205 |
| Calibrate: mineral stabilizing agent application rate. | Once using design rate per vane feeder. | Observe contractor calibration | .286 or .287 |
| Moisture: before injecting liquid bituminous material | 1 per 5,000 feet of lane of daily anticipated SFDR & one after the addition of water by the Contractor or mechanical drying out (disking, etc). | none | .281 / 105 |
| Yield: Mineral Stabilizing Agent and/or Liquid Bituminous Material | 1 per transport load each type | 1 per day each type | .286 & .287 / 402 & 403 |
| Compaction: Nuclear density for SFDR stabilized and CIR | 1 per 500 feet of lane width, (see note below) . | Observe the Contractor. | .282 |
| Control Strip: SFDR Stabilized and CIR | Minimum of once per project | Observe the Contractor. | |
| Bituminous Material Samples | none | Shall be a Certified Supplier - No Samples Required unless otherwise directed by the Engineer. | 1 quart each sample |
| Mineral Stabilizing Agent Samples | none | 1 sample | none |
| Foaming asphalt checks expansion ratio & half life | 1 per load | Observe the Contractor once per day. | .285 |
| Moisture (stabilized) - before placement of next layer during curing. | none | 3 daily after compaction. | Grading & Base Manual |

Note: The Engineer may require a Contractor to perform additional nuclear density tests in areas that the Engineer believes are failing density requirements.

GRADING AND BASE CONSTRUCTION ITEMS 1 of 3

| | | Material Type | Spec.* | Contractor / Producer QC Testing Rates | Minimum Required Agency QA Testing Rates | Verification Testing Sample |
|---------------------------------------|----------------------------------|--------------------------------------------------------------------------|----------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------|
| Gradation Testing (See Notes 2 & 3) | | Aggregate Surfacing | 2118 2211.5 | 1 / 1,000 CY (CV) stockpile gradation only required for materials on hand. Spec 1906.2 | > 250 CY or 500 Tons and < 2000 CY or 4000 tons. Material is a minimum of one lot. Test two random samples from each lot and average. > 2000 CY or 4000 Tons. Divide into lots with lot size no greater than 2000 CY/4000 Tons. Test two random samples from each lot and average. Determine individual results and lot averages for compliance (Table 2211-4 & 2211-5) | 1/source 30 lb. |
| | | Aggregate Base | 2211 2211.5 | | | |
| | | Shoulder Base Aggregate | 2221 2211.5 | | | |
| | | Drainable Aggregate Base (OGAB & DSB) | 2212 3136 | | | |
| | | Granular and Select Granular Material (borrow/embankment) | 3149.2B | 1/10,000 CY - req'd for mat'l on hand, Spec 1906.2 | 1/40,000 Cubic Yards - Compacted Volume - CV | 1/source 30 lb. |
| | | Stabilizing Aggregate | 3149.2C | | | |
| | | Reclamation FDR | 3135.2B | None | Test at Engineer's discretion. Look for oversize FDR, after the motor grader has overturned the material. | None |
| | | Granular Filter | 3601.2B | 1/source - before delivery on the project. | 1/ source | 1/source 30 lb. |
| | | Backfill Materials | 3149.2D | | | |
| | | Granular Bedding | 3149.2F | | | |
| | | Aggregate Bedding | 3149.2G | | | |
| | | Coarse Filter Agg. | 3149.2H | | | |
| | | Filter Aggregate | 3149.2J | | | |
| | Sand Cover | 3149.2K | | | | |
| Proctor | Sand Cone * Specified Density | Non-Granular Material per 2105.3F | 2105 2106 3149 | None | 1 per major soil, subgrade preparation specified density requires 100% of proctor density. | 1 sample 25 lb. |
| | | Non-Granular Material per 2105.3F | | AGENCY TESTING: Roadway Embankment: One test per 4,000 yd ³ (CV) <u>or if test rolled, One test per 8,000 yd³ (CV),</u> Transverse culverts & Abutments: 1 test per every 2 feet of fill per 250' of trench length. Structures Trenches: One test/500 feet of each structure length at various depths. Subgrade Preparation: One per 25 road stations. | | |
| Penetration Index Method (DCP) * | | Aggregate Base | 3138 2211.3C | None | 1 DCP tests per 500 yd ³ (CV) or 1 per 900 Tons. If test rolled, 1 test / 1,000 yd ³ (CV) or 1,800 Tons. | None |
| | | Shoulder Base Aggregate | | | | |
| | | Reclamation FDR & SFDR | 3135.2B 2215.2C | | 1 DCP test per 3,000 yd ² | |
| | | Granular Materials Subgrade Preparation (for materials meeting 3149.2B1) | 3149.2B | AGENCY TESTING: Roadway Embankment: One test per 2,000 yd ³ (CV) <u>or if test rolled, One test per 4,000 yd³ (CV),</u> Transverse culverts & Abutments: 1 test per every 5 feet of fill per 250' of trench length. Structures Trenches: One test/500 feet of each structure length at various depths. Subgrade Preparation: One per 25 road stations. | | |

[The Grading and Base Manual allows the nuclear density gauge, see pages 58 and 81.](#)

GRADING AND BASE CONSTRUCTION ITEMS 2 of 3

| | Material Type | Spec.* | Contractor / Producer QC Testing Rates | Minimum Required Agency QA Testing Rates | Verification Testing Sample |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------|----------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------|-----------------------------|
| Moisture Content Test During All Compaction Methods (see Note 4) | *Aggregate Base, Shoulder & Surfacing | 3138 | None | 1 / 1,000 yd ³ up to 10 Maximum | None |
| | Drainable Aggregate Base (OGAB & DSB) | | | | |
| | Reclamation FDR | 3135.2B | None | 1 / 10,000 yd ³ | |
| | All Embankment Materials | 3149 2105 | None | 1/10,000 yd ³ up to 10 Maximum | |
| | Subgrade Preparation | | | 1 per 25 road stations | |
| Percent Crushing | Particle Count (see note 1) | | 1 required for mat'l on hand, Spec 1906.2 | 1/ source unless directed by Engineer, (required for 3138.2B & C, 3149.2C & G1, 3136.2B Drainable Bases). | 1/source 30lb |
| Quality | Aggregate Quality Tests | 3138 3149 3601 | 1 required for mat'l on hand, Spec 1906.2 | 1/ source unless directed by Engineer | 1/source 30lb |
| Depth Check | Reclamation FDR | 3135.2B | 1/1,000 feet of machine width. | 1 per day unless directed by Engineer | |
| Test Rolling | Test Rolling (as directed in the special provisions) | 2111 | As directed by the Engineer the contractor will perform test rolling at the top of all subgrade, base layers (2211), non stabilized FDR (2215) and granular layers not meeting the requirements of 3149.2B2 (2105 & 2106). Minimum 12' width and 300' length. Agency to observe test rolling. See G & B Manual 5-692.270. | | |
| <p><u>Laboratory Samples are companion split samples to the QA sample:</u></p> <ul style="list-style-type: none"> -- Companion gradation, proctor, QA crushing, aggregate quality samples not required 1,000 tons or less. -- Include the laboratory companion with the first field sample. -- Include the field sample results with the laboratory sample. -- Laboratories with AMRL Accreditation are not required to submit laboratory companion samples. -- Carbonate aggregate materials require 50 lb. samples for the laboratory testing. | | | | | |
| NOTE 1: Percent crushing test is not required when the material is crushed from a quarry or contains 25% or greater recycled materials. | | | | | |
| NOTE 2: Submit a laboratory companion to the first Acceptance Gradation sample for a bituminous extraction, see 3138.2C. Full Depth Reclamation samples are not required. | | | | | |
| NOTE 3: The Certification of Aggregates and Granular Materials procedure and documentation of testing locations is at the discretion of the Engineer. | | | | | |
| NOTE 4: For quality compaction per spec 2105.3F2, test at Engineer's discretion. | | | | | |

* Review the Special Provisions. For granular materials, aggregate compaction will be by the "Penetration Index Method" unless otherwise designated in the plans or Special Provisions. Other compaction methods include the "Specified Density Method" (sand cone), "Quality Compaction Method" or "Light Weight Deflectometer Method. See 2211.3.D.2 Compaction. The Grading and Base Manual allows the nuclear density gauge, see pages 60 and 65.

Conversions: 1 ton = 0.55 yd³ (CV), 1 ton = 0.7 yd³ (LV), 1 yd³ (CV) = 1.8 tons.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

Samples are not required for less than 500 tons (250 CY).

GRADING AND BASE CONSTRUCTION ITEMS 3 of 3

Guidelines for Required Crushing & Aggregate Quality Tests

| | 3149 Granular Materials | 3138 Aggregate for Surface and Base | 3136 Drainable Bases |
|-------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------|
| Crushing | <p>Yes, for Stabilizing Aggregate, Fine Aggregate Bedding and Medium Filter Aggregate.</p> <p>Test waived if material contains recycled at twice the minimum crushing requirement.</p> <p>Not required for quarried sources.</p> | <p>Yes, for Class 5, 5Q & 6. Test waived if material contains recycled at twice the minimum crushing requirement.</p> <p>Not required for quarried sources. Class 2 must contain 100% crushed quarry rock.</p> | <p>Yes. Not required for quarried sources.</p> |
| Bitumen Content | <p>Yes, if it contains Bitumen</p> | <p>Yes, if it contains Bitumen</p> | Not applicable |
| LAR | Not applicable | <p>Yes, if source is carbonate quarry and does not contain bitumen.</p> | Yes |
| Insoluble Residue | <p>Yes, if source is carbonate quarry and does not contain bitumen.</p> | <p>Yes, if source is carbonate quarry and does not contain bitumen.</p> | <p>Yes, if source is carbonate quarry.</p> |
| Litho Exam & Shale Float Test | <p>Yes, for Medium Filter Aggregate</p> | <p>Yes, for Class 3, 4, 5, 5Q & 6, when not from quarried rock, and does not contain bitumen.</p> | <p>Yes, when not from a quarried source.</p> |

[Click here for testing procedures in the Grading & Base Manual.](#)

[Forms and worksheets at the Grading & Base Website.](#)

[Gradation worksheets at the SALT Construction Website](#)

CERTIFIED READY-MIX CONCRETE, 1 of 3

The Prime Contractor is responsible to assure that all ready-mix concrete used is produced by an annually Certified Ready-Mix plant as detailed in Specification 2461.3F.

| Material Spec. | Test Type (Concrete Manual) | Contractor / Producer QC Testing Rates when > 20 cy agency concrete produced per day. | | | | Form | |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------|------------------|----------------------|----------------------------------------------------------------------------------------------------------|
| bridge 2406.2 2411.2 2461.2 2461.3 general 2301** 2452.2 2461.2 2461.3 2506.2 2511.2 2514.2 2520.2 2521.2 2531.2 2533.2 2545.2 2554.2 2557.2 2564.2 2565.2 | Concrete Plant Production Testing Rates * | Gradation (5-694.145) (5-694.148) 3126, 3137 | For all JMF's (2461.2F.1.d) & bridge deck mix designs requires 1 per day or 1 per 400 yd ³ , whichever is greater. For all other mix designs: 1 or 2 days per week requires 1 per week or 1 per 400 yd ³ , whichever is greater. 3 or more days per week requires 2 per week or 1 per 400 yds ³ , whichever is greater. If weekly Agency production < 400 cy take a second sample on or after third day of production. Bridge Deck Concrete must have passing gradations prior to mixing. | | | | Concrete Agg. Work sheet, Agg. Grad. Control Charts, R-M Plant QC workbook |
| | | | Agency QA Testing Rates (1) Verification-companion to QC | | | | |
| | | | Coarse & Fine: a minimum of 1 per week per ready-mix plant*. | | | | |
| | | Moisture Content (5-694.142) | QC rates: | 1 every 4 hours | QA rates: | None | |
| | | Test Type | Agency QA Testing Rates (1) | | | | |
| | | Aggregate Quality (5-694.146) | Minimum of 1 per project per each fraction - use of MnDOT test results for the same 30 day time period is acceptable. <u>For bridge concrete:</u> 1 test each fraction per month. <u>For all bridge deck concrete poured during the month:</u> Test monthly quality to 3137.2D2 | | | | |
| | | Coarse Aggregate (% Passing 200) (5-694.146) | for each coarse aggregate fraction. Designate 3137.2D2 on the sample card. Gradation results will be included with the monthly quality tests. | | | | |
| | | Minimum Aggregate Sample Size *companion required, double sample size | | | | | |
| | | Aggregate Size | Gradation* | Quality* | Moisture | % -200 C.Agg | |
| | | 3/4" Plus, #4 | 25 lb. | 50 lb. | 2000 g | 12 lb. | |
| | | 3/4" Minus, #67 | 10 lb. | 30 lb. | 2000 g | 6 lb. | |
| | | #7, CA-70 | 6 lb. | 30 lb. | 2000 g | 6 lb. | |
| | | CA-80, #89 | 1.1 lb. (500 g) | 30 lb. | 500 g | 500 g | |
| | | Fine Aggregate | 1.1 lb. (500 g) | 30 lb. | 500 g | - | |
| | | Concrete Field Testing Rates | <u>Sampling Locations for Air, Slump, Temperature and Cylinder Testing</u> | | | | |
| First load each day per mix - Take sample after discharging approximately 1/4 yd ³ , stop further discharge until both slump and air content test are completed. The first load of concrete <u>must have passing air content and slump prior to placement</u> . Cast strength specimens from the same load as the air content and slump test. Test whenever adjustments are made to the mix. | | | | | | | |
| Subsequent tests - Sample from the middle portion of the load. | | | | | | | |
| Test Type | Agency QA Testing Rates (1) | | | | | | |
| Air Content - Type 3 Concrete (5-694.541) | 1 test per 100 yd ³ . Test first load each day per mix. Test when adjustments are made to the mix. | | | | | | |
| Slump (5-694.531) | Test first load each day per mix, then as necessary to verify passing slump. For Bridge Concrete: 1 test per 100 yd ³ . No testing required for slip form placement. | | | | | | |
| Air and Concrete Temperature (5-694.550) | Record temperature each time air content, slump or compressive strength specimen is performed/fabricated. | | | | | | |

CERTIFIED READY-MIX CONCRETE, 2 of 3

The Prime Contractor is responsible to assure that all ready-mix concrete used is produced by an annually Certified Ready-Mix plant as detailed in Specification 2461.3F.

| Spec. | Test Type | Agency QA Testing Rates (1) | Form | | |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------|
| bridge 2406.2 2411.2 2461.2 2461.3 general 2301** 2452.2 2461.2 2461.3 2506.2 2511.2 2514.2 2520.2 2521.2 2531.2 2533.2 2545.2 2554.2 2557.2 2564.2 2565.2 | Concrete Field Testing Rates | Compressive Strength (5-694.511) Standard cylinder size is 4 x 8, use 6 x 12 with aggregate greater than 1 1/4". Review 2461.3G.5 Test Methods and Specimens. | General Concrete Grades F, G, M, P, and R: 1 set of 3 cylinders per 300 yd ³ per mix per day. | 2409 Concrete Cylinder | |
| | | | Bridge Concrete Grades B, S, and Y: 1 set of 3 cylinders per 100 yd ³ , then 1 set of 3 cylinders per 300 yd ³ per mix per day | | |
| | | | Agency will break 1 set of 3 cylinders at 28 days. Agency will cast up to 3 control cylinders, any additional control cylinders are the responsibility of the Contractor. | | |
| | | | Cellular Concrete: 1 set of 4 cylinders (28 days) per day, fill in 2 equal lifts, <u>do not rod</u> , lightly tap the sides, cover and move to area with no vibration. Do not disturb for 24 hours. | | |
| | | 2506.2 2511.2 2514.2 2520.2 | Concrete Pavement Thickness ** | Observation of probing or coring at the Engineer's discretion. | 24327 |
| | | 2521.2 2531.2 2533.2 2545.2 2554.2 | Flexural Strength | Contractor: 1 beam (28 day) per day per mix. Make additional control beams as necessary. Control beams shall be made within the last hour of concrete poured each day. Fabricate beams, deliver beams to curing site, and clean beam boxes. Cylinders may be substituted for beams at the discretion of the Engineer. | 2162 Concrete Test Beam Data |
| | | 2557.2 2564.2 2565.2 | Concrete Pavement Texture | Contractor: Perform texture testing at locations determined by the Engineer in accordance with the Contract. The Contractor supplies all materials necessary to perform the required testing. | MIT SCAN T2 Report |

(1) - Review the requirements of 2461.3F Certified Ready-Mix Concrete, 2461.3G Concrete Placement and 5-694.010 Inspector's Checklist in the Concrete Manual.

***Small Quantity Requirements** are for less than 25 yd³ per week. Plant monitoring is not required but **Concrete Field Testing is required.**

**Concrete Pavement: Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly.

General Notes:

1. The testing rates shown in this Schedule of Materials Control are minimums. Take as many tests as necessary to ensure quality concrete. Should circumstances arise on a project which makes the testing rate impractical, contact the Concrete Engineering Unit.
2. All samples shall be taken in a random manner using an appropriate number generator.
3. The first load of concrete for any pour must have passing air content and slump results, prior to placing.
4. If batching or field adjustments are made, test the adjusted load for air content and if suspect, slump, before it gets into the work. The Engineer will determine if additional testing is required after each water adjustment made during slip form placement. Continue to test for air content and slump, if suspect, when test results are inconsistent or marginal.
5. If any field test fails, reject the concrete or if the Producer makes adjustments to the load to meet requirements, record the adjustments on the Certificate of Compliance. Retest the air content of the load, slump if required, and record the adjusted test results. Test the next load for air content and slump, if required, before it gets into the work.
6. Material not meeting requirements shall not knowingly be placed in the work. If failing concrete inadvertently gets placed in the work, review either the MnDOT Standard Specifications for Construction or contact the Concrete Engineering Unit for monetary deduction recommendations.

CERTIFIED READY-MIX CONCRETE, 3 of 3

The Prime Contractor is responsible to assure that all ready-mix concrete used is produced by an annually Certified Ready-Mix plant as detailed in Specification 2461.3F.

Best Practices:

1. It is recommended that the Agency Plant Monitor be present during critical pours, such as superstructure or paving concrete (i.e. 3A21, S mixes, JMF mixes).
2. It is recommended that the Agency representative continually monitor the progress of all concrete pours in the field and review Certificate of Compliances. It is not a recommended practice to only perform minimum testing requirements and leave the pour.
3. It is recommended to make standard strength cylinders after the first load of concrete unless that is the only load of concrete for that mix that day.
4. The Agency is responsible for verification sampling. For safety and consistency in sampling and splitting of the sample, it is recommended that the agency and the producer/contractor obtain the verification sample in tandem. This will allow the producer/contractor to witness the sampling process and take possession of the verification companion.

Concrete Plant and Field Materials

All materials must come from certified or qualified sources. All certified source must state so on the delivery invoices. The most current list of certified/approved sources can be found at MnDOT Material Website. Materials listed on the Approved Products List do not have to be sampled and need to be listed on the Material Acceptance Summary detailed in the SALT SMC. Samples can be submitted as directed by the Engineer.

| | Material | Spec. No. | Agency QA Minimum Required Field Sampling Rate | Form No. |
|--------------------------------------------------------------------------------------|----------------------------------------------------------------------------|-------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------|
| Concrete Plant Batching Materials | Portland Cement | 3101 | Shall be a Certified Supplier - For certified ready-mix and concrete paving sample rates: 1 sample when the plant is certified. Take additional samples at 6 months if producing Agency concrete, if the plant changes sources or as the contract requires. The producer obtains a 5 lb. sample and stores the sample in a sealed container provided by the Agency and includes the suppliers delivery invoice from which the sample is obtained. | 24300 ID Card Cement Samples |
| | Slag | 3102 | | |
| | Blended Cement | 3103 | | |
| | Fly Ash | 3115 | | 24308 Fly Ash |
| | Admixtures (Acceleration, Retarding, Water-Reducing, Air-Entraining, etc.) | 3113 | For all concrete: 1 sample in a 1/2 pint plastic container provided by the Agency when the plant is certified. Take additional samples at 3 months if producing Agency concrete, if the plant changes sources or as the contract requires. | 2410 Sample ID Card |
| | Water | 3906 | 1 sample in a 1 gallon clean glass or plastic container from a questionable source. | |
| Concrete Field Materials | Preformed Joint Filler | 3702 | Visual Inspection | 2410 Sample ID Card |
| | Preformed Elastomeric Type | 3721 | 1 per lot. Only materials from a qualified sources. Link to Approved Products List. | |
| | Silicone Joint Sealer | 3722 | | |
| | Hot Poured Elastomeric Type | 3723 3725 | | |
| | Burlap | 3751 | Visual Inspection | |
| | Paper | 3752 | Visual Inspection - Must be white opaque. | |
| | Membrane Curing Compound | 3754 3754AMS 3755 | Visual Inspection - Use only pre-approved curing compounds. | |
| | Plastic | 3756 | Visual Inspection - Must be white opaque and free from holes. | |
| Refer to the "Metals" schedule for sampling requirements for concrete reinforcement. | | | | |

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly.

2301 CONCRETE PAVEMENT - AGENCY 1 of 2 *

| Test Type (concrete manual) | Spec. | Concrete Paving Batch Plant Agency QA Testing | Certified Ready-Mix Plant Agency QA Testing | Form |
|-----------------------------------------------------------------------|-------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------|
| Gradation (1) (5-694.145) (5-694.148) | 3126 3137 | Test the first 4 QA samples of production each time the Contractor mobilizes the plant in a calendar year or changes aggregate sources. | | 21764 Agg Work sheet |
| | | 1 per day randomly thereafter. | 1 per 1000 yd ³ or 1 per week whichever is higher, randomly. | |
| Aggregate Moisture - QC Verification (2) (5-694.142) | 3126 3137 | <u>If w/c incentives apply:</u> 1 per 1000 yd ³ or every 4 hours, whichever is greater. Take initial sample within the first 250 yd ³ . | <u>If w/c incentives apply:</u> 1 per 200 yd ³ or every 4 hours, whichever is greater. Take initial sample within the first 100 yd ³ . | Concrete W/C Ratio Work sheet |
| Water Content, Microwave Oven Verification (3) (5-694.532) | Concrete Manual | Take initial sample within the first 250 yd ³ . At least one additional verification test should be taken if more than 1000 yd ³ is produced in a day. | Take initial sample within the first 100 yd ³ . At least one additional verification test should be taken if more than 400 yd ³ is produced in a day. | |
| Coarse Aggregate, -200 sieve (5-694.146) | 3137 | 1 randomly selected sample on the first day of production and each time the Contractor mobilizes the plant, changes the aggregate sources, or the cleanliness of the coarse aggregate is in question, then 1 per week randomly thereafter. -200 test may be performed at the lab instead at the plant at the discretion of the Engineer. | | 21764 Agg Work sheet |
| Coarse and Fine Aggregate Quality (4) | 3126 3137 | During concrete production: 1 randomly selected test each fraction every 20,000 yd ³ of production. Split the Quality sample 4 ways: 1) Provide 2 quarters of the sample to the producer/contractor. 2) Test the -200 on the coarse aggregate at the plant the day it was sampled. 3) Submit the remaining sample to the lab for quality testing including testing the -200 sieve on the coarse aggregate. | | 2410 Sample ID Card |
| Alkali Silica Reactivity (ASR) Testing | 2301 | 1 per paving project per sand source. Provide one 5 lb. sample of: cement, supplementary cementitious material (fly ash or slag), and sand. Write "Project Specific ASR Testing" on all 3 sample cards. ASR Testing is not required if the entire project is less than 3,500 cubic yards. | | 2410 24300 24308 |
| Coarse Aggregate Quality Testing of Incentive / Disincentive | 3137 | If coarse aggregate quality incentives apply: Test the Class B aggregates for % absorption and Class C aggregates for % carbonate including any other test necessary to make those determinations. Sample the 2 largest fractions in accordance with the following table and 2301: | | Coarse Agg Quality Incent / Disincent Work sheet |
| | | Coarse Aggregate Quality Incentive/Disincentive Sampling Rates | | |
| | | Plan Concrete Cubic Yards | Samples per fraction | |
| | | 3,500 - 7,500 | 3 | |
| | | 7,501 - 10,000 | 5 | |
| | | 10,001 - 25,000 | 10 | |
| | | 25,001 - 50,000 | 15 | |
| 50,001 + | 20 | | | |

*Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

Agencies using MnDOT Metro Inspection Services will be sampled at the current MnDOT Schedule of Materials Control rates and will be billed accordingly. Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

2301 CONCRETE PAVEMENT - AGENCY 2 of 2

| Test Type | Spec. | Concrete Field Testing - Agency QA Testing | Form |
|------------------------------------------------------|------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------|
| Air Content before consolidation for Type 3 concrete | Review Concrete Manual Website | 1 correlation air test per day | 2448 Weekly Concrete Report |
| Air Content after consolidation for Type 3 concrete | | 1 correlation air test per day | |
| Slump | | For fixed form placement: 1 slump test per day. For slip form placement: No slump testing required. | |
| Concrete Temperature | | Record temperature each time air content, slump or strength test specimen is performed/fabricated by the Agency. | |
| Flexural Strength | | Supply beam boxes, cure, and test beams. MnDOT standard beam box size is 6" x 6" x 20" unless other sizes or types are approved by the Concrete Engineer. | 2162 Test Beam Data |
| Concrete Pavement Texture | | Determine texture testing locations using random numbers. | Probing, Coring, Texture and MIT-Scan T2 Report |
| Thickness | | Determine probing and coring locations using random numbers. Initial pavement at core locations and re-initial the sides of specimens after coring to clearly verify their authenticity. | MIT-Scan T2 Report |
| Surface Smoothness /Dowel and Tie Bar Steel Location | | | Observe Contractor Testing when possible |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

NOTE (1): All gradation samples shall be taken in the presence of the Agency, unless otherwise authorized by the Engineer. All samples shall be taken off the belt leading to the weigh hopper unless otherwise approved by the Engineer. All gradations and quality tests require companion samples. If Coarse Aggregate Quality Incentive / Disincentives apply: The Agency may also use the QA samples for incentive / disincentive testing. Notify the producer to double the QC/QA sample size. **If well-graded aggregate incentives apply:** Use the Contractor's gradation results for well-graded aggregate incentive calculations as verified by Agency testing. Use the Well-graded Concrete Agg Worksheet.

NOTE (2): If w/c incentives apply: Use aggregate moisture results for determining the water content to calculate the w/c incentive / disincentive. Use the Concrete W/C Ratio Calculation Worksheet and do not leave sample unattended.

NOTE(3): If w/c incentives apply: Microwave oven verification testing to verify the w/c ration is completed in conjunction with Agency aggregate moisture testing. Do not leave samples unattended.

NOTE (4): Prior to concrete production: Obtain pre-production samples for quality testing at least 16 hours prior to concrete production. Samples may be taken from the stockpile and -200 test may be performed at the lab instead at the plant at the discretion of the Engineer. If the entire project is <3,500 yd³, pre-production sampling is not required.

| Minimum Aggregate Sample Size *companion required, double sample size | | | | |
|-----------------------------------------------------------------------|-----------------|----------|----------|--------------|
| Aggregate Size | Gradation* | Quality* | Moisture | % -200 C.Agg |
| 3/4" Plus, #4 | 25 lb. | 50 lb. | 2000 g | 12 lb. |
| 3/4" Minus, #67 | 10 lb. | 30 lb. | 2000 g | 6 lb. |
| #7, CA-70 | 6 lb. | 30 lb. | 2000 g | 6 lb. |
| CA-80, #89 | 1.1 lb. (500 g) | 30 lb. | 500 g | 500 g |
| Fine Aggregate | 1.1 lb. (500 g) | 30 lb. | 500 g | - |

CONCRETE PAVEMENT - PRODUCER / CONTRACTOR 1 of 2*

| Test Type (concrete manual) | Spec. | Concrete Paving Batch Plant Contractor/Producer QC Testing | Certified Ready-Mix Plant Contractor/Producer QC Testing | |
|------------------------------------------------------------------------------|------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------|--------------|
| Gradation (1) (5-694.145) (5-694.148) | 3126 3137 | When < 250 yd ³ produced 1 per day. When > 250 yd ³ produced/ day: 1 per 1500 yd ³ , or 1 per 1/2 day, whichever is the higher sampling rate. | When over 20 yd ³ produced per day: 1 per 400 yd ³ , or 1 per 1/2 day, whichever is the higher sampling rate. | |
| Coarse Aggregate -200 sieve (5-694.146) | 3137 | Test the first sample then at least 1 of the next 3 samples on the first day of production and each time the Contractor mobilizes the plant, changes the aggregate sources, or the cleanliness of the coarse aggregate is in question, then 1 per day randomly thereafter. Test these samples at the plant. | | |
| Aggregate Moisture QC Verification (2) (5-694.142) | 3126 3137 | If w/c incentives do not apply: 1 per 1000 yd ³ , or 1 completed every 4 hours, whichever is the higher sampling rate. | If w/c incentives do not apply: 1 completed every 4 hours. | |
| Water Content, Microwave Oven Verification | Review Concrete Manual | If w/c incentives apply: Obtain the plastic concrete sample at the plant. See Concrete Manual (5-694.532) | | |
| Unit Weight QC | | Test one load of concrete per day at the plant. See Concrete Manual (5-694.542) | | |
| Air Content QC (5-694.541) | | Test the first load of concrete at the plant | | |
| Coarse and Fine Aggregate Quality | 3126 3137 | Prior to concrete production: Test the Agency's pre-production sample at the Contractor's discretion. During concrete production: Test the -200 on the quality companion sample the day it was sampled. All other testing is at the Contractor's discretion. | | |
| Coarse Aggregate Quality Testing for Incentive / Disincentive | 3137 | Test at the Contractor's discretion. | | |
| Minimum Aggregate Sample Size *companion required, double sample size | | | | |
| Aggregate Size | Gradation* | Quality* | Moisture | % -200 C.Agg |
| 3/4" Plus, #4 | 25 lb. | 50 lb. | 2000 g | 10 lb. |
| 3/4" Minus, #67 | 25 lb. | 30 lb. | 2000 g | 6 lb. |
| #7, CA-70 | 6 lb. | 30 lb. | 2000 g | 6 lb. |
| CA-80, #89 | 1.1 lb. (500 g) | 30 lb. | 500 g | - |
| Fine Aggregate | 1.1 lb. (500 g) | 30 lb. | 500 g | - |

* Use Certified Ready-Mix Concrete testing rates when: a) The entire concrete paving project is less than 3,500 cu.yd. b) When a secondary plant is used to provide minor work.

NOTE (1): Performing testing on representative material at the end of the most recent day of production is allowed. If well-graded aggregate incentives apply: Use the Contractor's gradation results for well-graded aggregate incentive calculations as verified by Agency testing.

NOTE (2): Complete the initial moisture content and adjust the batch water prior to the start of concrete production each day. If weather conditions allow, performing moisture testing on representative material at the end of production the prior evening is allowed.

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

CONCRETE PAVEMENT - PRODUCER / CONTRACTOR 2 of 2

| Test Type | Spec. | Concrete Field Testing - Contractor QC Testing |
|------------------------------------------------------|------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Air Content before consolidation for Type 3 concrete | Review Concrete Manual Website | 1 per 300 yd ³ or 1 per hour, whichever is less. Test first load each day per mix. |
| Air Content after consolidation for Type 3 concrete | | Test 1 air content per 1/2 day per mix of slip form paving to establish an air loss correction factor (ACF). See Special Provisions for additional information. |
| Slump | | For fixed form placement: 1 per 300 yd ³ and as directed by the Engineer. Test first load each day per mix. For slip form placement: No slump testing required. |
| Concrete Temperature | | Record temperature each time air content, slump or strength test specimen is performed/fabricated by the Contractor. |
| Flexural Strength | | 1 beam (28 day) per day per mix. Make additional control beams as necessary. Control beams shall be made within the last hour of concrete poured each day. Fabricate beams, deliver beams to curing site, and clean beam boxes. Cylinders may be substituted for beams at the discretion of the Engineer. |
| Concrete Pavement Texture | | Perform texture testing at locations determined by the Engineer in accordance with the Contract. All adjoining lanes shall be tested at the same location if paved at the same time. The Contractor supplies all materials necessary to perform the required testing. |
| Thickness | | The Contractor drills concrete cores at locations determined by the Agency. The Contractor probes the plastic concrete at locations determined by the Agency. |
| Surface Smoothness | | Contractor provides MnDOT certified inertial profiler results for the entire project as required by the contract. Check for current certification. |
| Dowel Bar and Tie Bar Steel Location | | On the first day and each day of pavement: (1) Verify the adequacy of the dowel bar anchoring by scanning seven random doweled contraction joints in each subplot. (2) Verify the presence and alignment of tie bar steel by scanning 75 lin. Ft. in each subplot. If the Engineer determines the first days dowel bar anchoring and tie bar placement processes are acceptable, the Engineer may allow a reduction in scanned joints in each subplot as follows: (1) Verify the adequacy of the dowel bar anchoring by scanning four random doweled contraction joints per subplot. (2) Verify the presence and alignment of tie bar steel by scanning 25 lin. ft. out of every subplot. |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

2404 CONCRETE WEARING COURSE FOR BRIDGES

| Test Type (concrete manual) | Spec. | Contractor/Producer QC Testing | Agency QA Testing | Form |
|-----------------------------------------------------------------------------------------------------------|------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------|
| Gradation, Quality, Coarse Agg -200 QC/Verification (5-694.145) (5-694.146) (5-694.148) | 3126 3137 | Prior to production, provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. Test Agency companion samples are Contractor's discretion. | 1 per fraction prior to production and each time aggregate is delivered to the site. | 2410 Sample ID Card |
| Air Content - Type 3 Concrete (Verification) (5-694.541) | Review Concrete Manual Website | None | 1 per 15 yd ³ , Test at beginning of pour each day. | Weekly Report of Low Slump Concrete |
| Slump (Verification) (5-694.531) | | None | 1 per 15 yd ³ , Test at beginning of pour each day. Allow mix to hydrate 5 minutes before slump test to assure all cement is saturated. | |
| Compressive Strength (5-694.511) | | None | 1 cylinder (28 day) per 30 yd ³ | 2409 Cyl. ID Card |

| Test | Minimum Sample Size *companion req'd, double sample size | |
|-----------|----------------------------------------------------------|-----------------------|
| Gradation | 6 lb. for # 7, 500 g for CA-80 | 50 g for Sand |
| Quality | 30 lb. for Coarse Aggregate | 30 lb. Fine Aggregate |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

CONCRETE PAVEMENT REPAIR - CPR for 3U18

| Test Type | Spec. | Contractor/Producer QC Testing | Agency QA Testing | Forms |
|-------------------------------------|------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------|
| Gradation, Quality, Coarse Agg -200 | 3126 3137 | Prior to production, the Contractor shall provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. No quality test results are required. Test companion samples at Contractor's discretion. | Gradation: 1 per aggregate fraction prior to production and each time aggregate is delivered to the site. Quality Testing & Coarse Agg - 200: 1 test per aggregate fraction per source. The Agency may use the gradation results for the Quality Samples as a substitute for 1 required field gradation. | 2410 Sample ID Card |
| Air Content - Type 3 Concrete | Review Concrete Manual Website | None | 1 per 15 yd ³ , Test at beginning of pour each day. | 21412 Weekly Report of Low Slump Concrete |
| Slump | | None | 1 per 15 yd ³ , Test at beginning of pour each day. Allow mix to hydrate 5 minutes before slump test to assure all cement is saturated. | |
| Compressive Strength | | None | 1 cylinder (28 day) per 30 yd ³ | 2409 Cyl. ID Card |

| Test | Minimum Sample Size *companion req'd, double sample size | |
|-----------|----------------------------------------------------------|-----------------------|
| Gradation | 6 lb. for # 7, 500 g for CA-80 | 50 g for Sand |
| Quality | 30 lb. for Coarse Aggregate | 30 lb. Fine Aggregate |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

DOWEL BAR RETROFIT - DBR

| Test Type | Spec. | Contractor/Producer QC Testing | Agency QA Testing | Form |
|-------------------------------------|--------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------|---------------------|
| Gradation, Quality, Coarse Agg -200 | 3126 3137 | Prior to production, the Contractor shall provide the Agency with: Aggregate pit numbers, 1 passing gradation result per fraction per source. No quality test results are required. Test companion samples are Contractor's discretion. | 1 per fraction prior to production and each time aggregate is delivered to the site. | 2410 Sample ID Card |

| Test Type | Spec. | Agency QA Testing | Form |
|-----------------------------------|----------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------|
| DBR Material Compressive Strength | Review Concrete Manual | Contractor Testing: None | 2409 Cylinder ID Card |
| | | Agency Testing: During the pre-production test operations: 1 set of 3 cylinders tested at a rate as directed by the Engineer. Testing may need to be repeated if any problems with the dowel bar retrofit material are encountered. First day of production: 1 set of 3 cylinders at a rate directed by the Concrete Engineer. After the first day of production: 1 cylinder per day during production tested at a rate determined by the Engineer to determine traffic strength. | |

| Test | Minimum Sample Size *companion req'd, double sample size | |
|-----------|----------------------------------------------------------|-----------------------|
| Gradation | 500 g for # 89 & Sand | |
| Quality | 30 lb. Coarse Aggregate | 30 lb. Fine Aggregate |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

LANDSCAPING AND EROSION CONTROL ITEMS

| Kind of Material | Spec. # | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|------------------------------------------------------------------|----------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Manufactured Topsoil Borrow, Salvaged Topsoil (stockpiled) | 3877.2 | As directed by the Engineer |
| Plant Stock & Landscape Materials | 3861 and 2571.2A1 | Materials must be in accordance with the Inspection and Contract Administration Guidelines for MnDOT Landscape Projects of which determines the minimum and maximum criteria thresholds. Certificate of Compliance, Nursery stock certificate registered with Mn Dept. of Agriculture. Out of state products subject to pest quarantines must accompanied by documentation certifying all products are free of regulated pests. |
| Erosion Control Blanket | 3885 | Visual Inspection and Check approved products or approved vendors list - As directed by the Engineer. |
| Erosion Control Netting | 3885 | |
| Silt Fence | 3886 | |
| Erosion Stabilization Mat | 3885 | |
| Flotation Silt Curtain | 3887 | Accepted, based on manufacturers certification of compliance. Check weight of fabric. |
| Filter Logs | 3897 | Visual Inspection |
| Flocculants | 3898 | Obtain copy of Certificate of Compliance and MSDS |
| Fertilizer | 3881 | Obtain copy of invoice of blended material stating analysis. |
| Agricultural Lime | 3879 | Contractor must supply amount of ENP (Equivalent Neutralizing Power) for each shipment. |
| Mulch - Type 3 | 3882 | Certified Weed Free (Certified sources only) Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA). |
| Mulch - Type 6 - Woodchips | | All wood chips supplied by a supplier outside the Emerald Ash Borer quarantine area or have an Emerald Ash Borer Compliance Agreement with the MDA |
| Seeds | 3876 | (Certified Vendors Only) (Mixes 100-299) Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA). |
| Native Seed | | (Mixes 300-399) certified seed only. Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA). |
| Sod | 3878 | Visual Inspection - Check approved products list - As directed by the Engineer. Check for Certified Vendor tag from Minnesota Crop Improvement Association (MCIA) for salt tolerant sod. |
| Compost (from Certified Source) | 3890 | |
| Compost (from Non-Certified Source) | | Visual Inspection - As directed by the Engineer. |
| Hydraulic Soil Stabilizer | 3884 | Check Approved/Qualified Products List - As directed by the Engineer. |

Contact the MnDOT District IA Inspector to provide servicing of your Federal Aid Project.

CHEMICAL ITEMS

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|-------------------------------------------------------|----------------------|-------------------------------------------------------------------------------------------------------|
| Asphalt Plank | 3204 | Visual Inspection - As directed by the Engineer. |
| Calcium Chloride | 3911 | Review the percentage required as per specification. Check for listing on Qualified Products website. |
| Magnesium Chloride | 3912 | |
| Hot-Pour Crack Sealant (for Crack Sealing/Filling) | 3719 3723 3725 | Retain Certification of Compliance. Check for listing on Qualified Products website. |
| Pavement Joint Adhesive | Special Provisions | Retain Certification of Compliance |
| Waterproofing Materials | | |
| Membrane Waterproofing System | 3757 | Visual Inspection - Check qualified products list. |
| Waterproofing Materials - Three Ply System | | |
| Asphalt Primer | 3165 | Verify supplied material meets ASTM D 41 |
| Waterproofing Asphalt | 3166 | Verify supplied material meets ASTM D 449 |
| Fabric | 3201 | Verify supplied material meets ASTM D 41 |
| Paints | | |
| Waterborne Latex - Traffic Paint | 3591 | Visual Inspection - Check qualified products list - retain Certificate of Compliance. |
| Epoxy Traffic Paint | 3590 | |
| Traffic Marking Paint | Special Provisions | |
| Non-Traffic Striping Paints | 3500 Series | Retain Certification of Compliance |
| Bridge Structural Steel Paint | 3520 | Visual Inspection - Check approved products list - retain Certificate of Compliance. |
| Exterior Masonry Paint | 3584 | |
| Noise Wall Stain | Special Provisions | |
| Drop-on Glass Beads | 3592 | Visual Inspection - Check qualified products list. Retain Certificate of Compliance. |
| Pavement Marking Tape | 3354 | Visual Inspection - Check qualified products list. Retain Certificate of Compliance. |
| | 3355 | |
| | Special Provisions | |
| Signs and Markers | 3352 | Visual Inspection - Check qualified products list. |

Metals 1 of 2

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) * |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Guard Rail | | |
| Fittings - Splicers, Bolts, Posts etc. | 3381 | Visual Inspection - Materials shall be approved before use. Call MnDOT inspector at 218-846-3613 to see if material has been approved. |
| Structural Plate Beam | 3382 | |
| Non-High Tension Guard Rail Cable | 3381 | |
| High Tension Guard Rail Cable | Special Provisions | |
| Steel Posts | | |
| Steel Sign Posts | 3401 | Visual Inspection - As directed by the Engineer. Retain Certificate of Compliance in Project file. |
| Fence Posts, Brace Bars, Rails and others | 3403 | Visual Inspection - As directed by the Engineer. Retain Certificate of Compliance and certified mill analysis in project file. |
| | 3406 | |
| | 3379 | |
| Fence | | |
| Barbed Wire | 3376 | Visual Inspection Retain Certification of Compliance, As directed by the Engineer. |
| Woven Wire | | |
| Chain Link Fabric | | |
| Components: cup, cap, nut, bolt, end clamp, tension band, truss rod tightener, hog ring, tie wire, tension stretcher bar, truss rod, clamp & tension wire | | |
| Gates | 3379 | |
| Pipe | | |
| Water Pipe and other Piping Materials | 3364, 3365, 3366 & Special Provisions | Visual Inspection - As directed by the Engineer. |
| Reinforcing Steel - Inspected by MnDOT & will be charged back to the Local Agency. | | |
| Uncoated Bars | 3301 | Retain Certificate of Compliance & Certified Mill Analysis |
| Epoxy Coated Bars | 3301 | For Epoxy-Coated bars, steel will be tagged "Inspected" when it has been sampled and tested by Mn/DOT prior to shipment, & it will be tagged "Sampled" when testing has not been completed prior to shipment. If the Epoxy-Coated bars are not tagged "Sampled" or "Inspected", submit samples (1 bar 3ft long for each size for each day's coating production), Certificate of Compliance, & Certified Mill Analysis for testing. Maintain original Cert. of Compliance & Certified Mill Analysis in project file. |
| Spirals | 3305 | |
| Stainless Steel Bars | Special Provisions | Visual Inspection Testing as directed by the Engineer (2 bars 3 ft. long per heat per bar size). Certified Mill Test Reports to be filed. |

Metals 2 of 2

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) * | |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------|
| Reinforcing Steel - Inspected by MnDOT & will be charged back to the Local Agency. | | | |
| Steel Fabric | 3303 | 2 sq ft if epoxy coated. | Visual Inspection - Retain Certificate of Compliance. |
| Dowel Bars | 3302 | One dowel bar and basket from each shipment. | |
| Prestress/Post Tension Strands | 3348 Spec.Prov. | One sample of 2 strands by 6 ft from each heat/production lot. | |
| Castings | | | |
| <u>Drainage Castings</u> | 3321 | Visual Inspection - Check approved / qualified list. | |
| | 2471 | | |
| <u>Electrical</u> | 2565 | | |
| Anchor Rods (Cast in Place) and Structural Fasteners | 3385 3391 | Visual Inspection - Check approved / qualified list. Testing as directed by the Engineer, (see Notes below) | |
| Notes: Manufacturer must have one yearly passing test from the Department for each anchor rod or bolt type. Prior to installation, obtain copy of Mn/DOT passing test report from supplier. Specs 3385.2 A, B, & C require anchor rod markings per ASTM F 1554 S3. The end of each anchor bolt intended to project from the concrete must be die stamped with the grade identification as follows: Grade 36 = AB36, Grade 55 = AB55, Grade 105 = AB105. | | | |
| <u>Anchorage (Drilled In)</u> | Special Provisions | Visual Inspection - Check qualified products list. | |
| <u>Structural Steel</u> | Inspected by MnDOT & will be charged back to the Local Agency. | | |
| Steel Bridge - Beams, Girders, Diaphragms, etc. | 2471 | Structural Metals Inspection Tag and field inspection for damage/defects, check dimensions for contract compliance. Review approved products list as directed by the Engineer. Note: Structural metals products will be inspected at the plant and will be shipped with a Structural Metals Inspection Tag. An inspection confirmation report will be completed by Structural Metals Inspection staff and sent to the field personnel. Only approved suppliers are allowed to supply Structural Metals products. A list of approved suppliers can be found on the Bridge Office web site: http://www.dot.state.mn.us/bridge/ | |
| Concrete Girders-Diaphragms and sole plates | | | |
| Expansion Joints | | | |
| Steel Bearings | | | |
| Railing-Structural tube and ornamental | | | |
| Drainage Systems | | | |
| Protection Angles | | | |
| Overhead Sign structures | | | |
| High Mast Lighting Structures | 2545 2471 | | |
| Monotube Signal Structures | 2565 2471 | | |

* Check domestic steel requirement under 1601 Special Provision.

Geosynthetics, Pipe, Tile, Precast/Prestressed Concrete

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|---------------------------------------------------------------------------------------------------------------------|-----------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Corrugated Metal Products | | |
| Culvert Pipe Under drains Erosion control Structures | 3225 thru 3229, 3351, 3399 | Make certain pipe is Certified on Invoice, retain certificate of compliance and certified mill analysis in project file. Retain the Certificate of Compliance and certified mill analysis in project file. |
| Structural Plate | 3231 | |
| Aluminum Structural Plate | 3233 | |
| Pipe | | |
| Clay Pipe | 3251 | Visual Inspection |
| Reinforced Concrete Pipe and Arches, Precast Cattle Pass Units, Sectional Manhole Units | 3236 | Field Inspection: Check for damage and defects. Check dimensions and class as required. |
| Non-Reinforced Concrete Pipe | 3253 | |
| Drain Tile (Clay or Concrete) | 3276 | Visual Inspection - Acceptance as directed by the Engineer. |
| Thermoplastic (TP) Pipe ABS and PVC | 3245 | Obtain Certificate of compliance. Check for approved marking printed on pipe. Field Inspect for damage or defects. |
| Corrugated Polyethylene Pipe | 3278 | Check for markings (AASHTO M 252) Certificate of Compliance. Field Inspect for damage or defects. |
| Corrugated Polyethylene Pipe - Dual Wall 12"-48" | 3247 | Visual Inspection - Check approved products list. Obtain Certificate of Compliance. |
| Precast/Prestressed Concrete Structures - Inspected by MnDOT & will be charged back to the Local Agency. | | |
| Reinforced Precast Box Culvert | 3238 | Field Inspection: Check for damage and defects. Check dimensions as required. Check for the "MnDOT" stamp and signature on the certification document. |
| Precast/Prestressed Concrete Structure (beams, posts, etc.) | 2405 | |
| Manholes and Catch Basins (Construction) | 2506 3622 | |
| Sewer Joint Sealing Compound | 3724 | Visual Inspection - Acceptance as directed by the Engineer. |
| Preformed Plastic Sealer for Pipe | 3726 Type b | Visual Inspection - Acceptance as directed by the Engineer. |
| Bituminous Mastic Joint Sealer for Pipe | 3728 | |
| EPS Geofoam | Special Provisions | Visual Inspection - Acceptance as directed by the Engineer. Check for yellow aged material, uniformity and dimensions. |
| Geotextile Fabric and Geogrid Reinforcement | 3733 and Special Provisions | Obtain Certificate of Compliance stating minimum average roll values (MARV). MARV must meet Project requirements. Fabric must be listed on Geotextile Small Quantity Acceptance List available at http://www.dot.state.mn.us/materials/aggregatedocs/gtxlist.pdf |
| Geotextile Small Quantity Acceptance List | | |
| Silt Fence | 3886 | Visual Inspection - Check approved products list. |

ELECTRICAL AND SIGNAL EQUIPMENT ITEMS 1 of 2

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|------------------------------------------------------|--------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Lighting Standards (Aluminum or Steel) | 3811 | Visual Inspection - Obtain Certificate of Compliance. The Fabricator will submit "Certificate of Compliance", on a per project basis, to the Project Engineer. |
| Hand Holes (Precast, PVC, and LLDPE) | 2545 | Visual Inspection - Check approved/qualified products list. Traffic signal and street lighting projects require hand holes to be listed on the Mn/DOT Signals Approved Products List (APL). For cast iron frame and cover: see Metals - Drainage and Electrical Castings |
| | 2550 | |
| | 2565 | |
| Foundation | 2545 | Slump as needed, 1 cylinder per 25 cu.yds. Rebar is required in concrete foundations as specified in the Contract documents for all traffic control signals and roadway lighting projects. |
| Steel Screw In Foundations | 2545 2565 | See Approved/Qualified Products List for Roadway Lighting and Signals. |
| Conduit and Fittings | | |
| Metallic | 3801 | Visual Inspection - Conduit shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL). For traffic signal and street lighting projects, specific requirements are contained in the Special Provisions for each project. |
| | 3802 | |
| Non-Metallic (Rigid and HDPE) | 3803 | |
| | Special Provisions | |
| Anchor Rods and Bolts (Cast in Place) | 3385 | Visual Inspection - Manufacturer must have one yearly passing test from the Department for each anchor rod or bolt type. Prior to installation, obtain copy of Mn/DOT passing test report from supplier. Specs 3385.2 A, B, & C require anchor rod markings per ASTM F 1554 S3. The end of each anchor bolt intended to project from the concrete must be die stamped with the grade identification as follows: Grade 36 = AB36, Grade 55 = AB55, Grade 105 = AB105. |
| Anchorages (Drilled In) | Special Provision | Visual Inspection - Check qualified products list. |
| Miscellaneous Hardware | 2545 2565 | Visual Inspection - Check approved products list. Will carry "Inspected" tag if sampled and tested prior to shipment. No sample necessary if "Inspected". Do not use if not tested. Field sample at sampling rate for laboratory testing. For traffic signal and street light lighting projects, various miscellaneous hardware is required to be listed on the Mn/DOT Signals and Lighting Approved Products Lists (APL). The Contract documents indicate, which items must be on the Signals and/or Lighting APL. |
| Cable and Conductors | | |
| Power Conductors | 3815.2B1 | Visual Inspection - Make certain the conductors are the type specified. Submit Field Inspection report showing type and quantities used. Shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL) and type where applicable. |
| Loop Detector Conductors (No Tubing) | 3815.2B2 (a) | |

ELECTRICAL AND SIGNAL EQUIPMENT ITEMS 2 of 2

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|-----------------------------------------------------|-------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Electrical Cables and Single Conductors with Jacket | 3815.2B2(b) 3815.2B3 | Visual Inspection - Usually inspected at the distributor. Documentation showing project number, reel number(s), & Mn/DOT test number(s) will be included with each project shipment. If such documentation is not received from Contractor, submit sample for testing along with material certification from manufacturer. Do not use if not tested. Pre-inspected materials will not be tagged; an inspection report will be sent by the Mn/DOT inspector for each shipment. Project inspectors should verify that the shipping documents agree with this inspection report. Call Steve Grover at 651-366-5540 or Cindy Schellack at 651-366-5543 with questions. For traffic signal and street lighting projects, the Special Provisions for each project contain electrical cable and conductor specifications. |
| | 3815.2B5 | |
| | 3815.2C1 thru .2C8 | |
| | 3815.2C14 | |
| | Special Provisions | |
| Fiber Optic Cables | 3815.2C13 | Visual Inspection - Check approved products list for Traffic Management Systems. |
| Ground Rods | 2545 | Visual Inspection - Check approved products list. Shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL). Detail materials on Materials Acceptance Summary. |
| | 2565 | |
| Luminaires and Lamps | 3810 | Visual Inspection - Check approved products list. Traffic signal and street lighting projects require luminaires and lamps to be listed on the Mn/DOT Lighting Approved/Qualified Products List (APL). The conductors shall be labeled as being listed by a National Recognized Testing Laboratory (NRTL) and type, where applicable. |
| Electrical Systems | 2565 | Electrical Systems are to be reported as a "System" using the LIGHTING, SIGNAL AND TRAFFIC RECORDER INSPECTION REPORT. To be certified by the Project Engineer. |
| Traffic Signal Systems | 2565 | Traffic Signal Systems are to be reported as a "System" using the LIGHTING, SIGNAL AND TRAFFIC RECORDER INSPECTION REPORT. To be certified by the Project Engineer. |

Brick, Stone and Masonry Units

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Brick | | |
| Sewer (clay) and Building | 3612 to 3615 | Visual Inspection - Acceptance as directed by the Engineer. |
| Sewer (Concrete) | 3616 | Visual Inspection - Acceptance as directed by the Engineer. Air entrainment required. Obtain air content statement from supplier. |
| Concrete Masonry Units | | |
| Sewer Construction | 3621 | Visual Inspection - Acceptance as directed by the Engineer. Air entrainment required. Obtain air content statement from supplier. |
| <u>Modular Block Retaining Walls</u> | Review Current Special Provisions | Visual Inspection - Note: All lots of block upon delivery shall have Manufacturer or Independent laboratory test results to verify passing both compression and freeze-thaw requirements. * Wall units and cap units are considered separate block types. |
| Reinforced Concrete Cribbing | 3661 | Visual Inspection - Acceptance as directed by the Engineer. Will be stamped when inspected prior to shipment. |
| Stone for Masonry or Rip Rap | 3601 and Special Provisions | Visual Inspection - Acceptance as directed by the Engineer. |
| REMARKS: Each source shall be approved by Project Engineer or Supervisor for quality, prior to use. For questions on quality, contact District Materials or Geology Unit. | | |

Miscellaneous Materials

| Kind of Material | Spec. No. | Minimum Required Agency QA Acceptance Testing (Field Testing Rate) |
|------------------------------------------------|-----------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Timber, Lumber Piling & Posts | 3412 to 3471 & 3491 | Visual Inspection - Acceptance as directed by the Engineer. Untreated materials shall be inspected in the field. Treated materials shall be Certified on the Invoice or Shipping Ticket. Material is inspected and stamped by an Independent Agency as per Specification 3491. Contact Laboratory for additional information. |
| Miscellaneous pieces and Hardware (Galvanized) | 3392 3394 | Visual Inspection - Acceptance as directed by the Engineer. |
| Insulation Board | 3760 | |
| Elastomeric Bearing Pads - Plain or Laminated | 3741 and Special Provisions | Check dimensions. Check repair of tested pad. Obtain copy of Certificate of Compliance. DO NOT USE ANY PADS THAT ARE NOT CERTIFIED. |
| Cotton Duck Bearing Pads | | |

Approved/Qualified Products

Asphalt Products

Bridge Products

Concrete Products

Crack & Joint Materials Products

Truncated Domes

Drainage

Erosion Control and Landscaping Products

Geosynthetics

Maintenance Shop Supplies

Pavement Markings

Paint/Stain/Coating Systems (Non-Pavement)

Precast Concrete

Roadside Barriers

Roadway Lighting Products

Signals Products

Signing Products

Snow and Ice Chemical Products

Temporary Traffic Control Devices

Traffic Management Systems/ITS

Vehicle Safety Lighting

Walls (Retaining/Noise)

SALT Construction Website - Additional Resources

Bituminous Engineering

Asphalt Binder Certified Supplier

Asphalt Emulsion Certified Supplier

Concrete Engineering

MnDOT Concrete Manual

QC & QA RM Plant Workbooks

MnDOT Certified Ready-Mix Program

Grading & Base Engineering

Testing procedures in the Grading & Base Manual.

Forms and worksheets at the Grading & Base Website.

Gradation worksheets at the SALT Construction Website

SALT SMC - LGA Contacts

Districts 1, 2, 3, 4

Ron Bumann - State Aid Construction Specialist

ronald.bumann@state.mn.us

218-725-2811

Districts 6, 7, 8

Rollin Larson - State Aid Construction Specialist

rollin.larson@state.mn.us

507-205-6403

Metro

Michael Pretel, PE

State Aid Construction Engineer

MNDOT Metro District

651 234 7778

michael.pretel@state.mn.us

Jim Deeny - State Aid Construction Liaison

james.deeny@state.mn.us

651-234-7762

Telephone Index for MnDOT Specialty Offices

Grading & Base

| | | |
|---------------|----------------|----------------|
| Terry Beaudry | G&B Engineer | (651) 366-5456 |
| John Bormann | G&B Specialist | (651) 366-5496 |

www.dot.state.mn.us/materials/gradingandbase.html

Bituminous

| | | |
|----------------|------------------------|----------------|
| John Garrity | Bituminous Engineer | (651) 366-5577 |
| Greg Johnson | Asst Bit Engineer | (651) 366-5464 |
| Greg Schneider | Asst Bit Engineer | (651) 366-5403 |
| Elliot Keyes | Pavement Preserv Eng | (651) 366-5432 |
| Deb Evans | Bit Eng Specialist | (651) 366-5574 |
| Ray Betts | Bit Trial Mix Lab Tech | (651) 366-5469 |

See Bituminous website for the contact list by topic

www.dot.state.mn.us/materials/bituminous.html

Concrete

| | | |
|--------------|---------------------------|----------------|
| Maria Masten | Concrete Engineer | (651) 366-5572 |
| Ron Mulvaney | Structural Conc Eng | (651) 366-5575 |
| Rob Golish | Asst Concrete Eng | (651) 366-5576 |
| Wendy Garr | Concrete Eng Specialist | (651) 366-5423 |
| Gordy Bruhn | Conc Field Eng Specialist | (651) 366-5523 |

See Concrete website for the contact list by topic

www.dot.state.mn.us/materials/concrete.html

Contacts for other materials can be found on the
Materials and Road Research Contacts page.

<http://www.dot.state.mn.us/materials/contacts.html>

Contacts for Approved Products can be found
at the Approved/Qualified products Contact page.

<http://www.dot.state.mn.us/products/contacts.html>

Materials Lab. Contacts

Independent Assurance

| | | | | | | | | | | | |
|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------|----------------|---------------------|----------------|-------------|----------------|-------------------|----------------|------------|----------------|
| <p>District 1, Duluth Leila DeLuca 218-725-2738 Fax 218-725-2800</p> | <p>Nadine Miller (218) 725-2737 Cell (218) 348-6297</p> | | | | | | | | | | |
| <p>District 2, Bemidji Jeff Long, 218-755-6544 Jason Kisse, 218-755-6542 Fax 218-755-6540</p> | <p>Thomas Lloyd (218) 755-6545 Cell (218) 766-6949</p> | | | | | | | | | | |
| <p>District 3A, Baxter Tom Boser, 218-828-5755 Fax 218-828-5816</p> | <p>Matt Miles (218) 828-5753 Cell (218)232-6748</p> | | | | | | | | | | |
| <p>District 3B, Saint Cloud Teresa Mertens, 320-223-6555 Fax 320-223-6582</p> | <p>Teresa Mertens (320) 223-6555 Cell (320) 493-3559</p> | | | | | | | | | | |
| <p>District 4, Detroit Lakes Brad Hanson, 218-846-3616 Bruce Bryngelson, 218-846-3614 Wayne Koons, 218-846-3617 Fax 218-846-0744</p> | <p>David Brunner (218) 846-3613 Cell (218) 849-7393</p> | | | | | | | | | | |
| <p>Metro District, Maplewood Lab Mike Evans, 651-366-5409 Fax 651-366-5408</p> | <table border="0"> <tr> <td data-bbox="881 1083 1133 1119">Waters Edge Mat'ls</td> <td data-bbox="1133 1083 1378 1119">(651) 234-7356</td> </tr> <tr> <td data-bbox="881 1119 1133 1155">East Steve Reinardy</td> <td data-bbox="1133 1119 1378 1155">(651) 755-1581</td> </tr> <tr> <td data-bbox="881 1155 1133 1190">Mike Herbst</td> <td data-bbox="1133 1155 1378 1190">(651) 775-1018</td> </tr> <tr> <td data-bbox="881 1190 1133 1226">West Greg Bohmert</td> <td data-bbox="1133 1190 1378 1226">(651) 775-1005</td> </tr> <tr> <td data-bbox="881 1226 1133 1276">Mike Amiot</td> <td data-bbox="1133 1226 1378 1276">(651) 775-1042</td> </tr> </table> | Waters Edge Mat'ls | (651) 234-7356 | East Steve Reinardy | (651) 755-1581 | Mike Herbst | (651) 775-1018 | West Greg Bohmert | (651) 775-1005 | Mike Amiot | (651) 775-1042 |
| Waters Edge Mat'ls | (651) 234-7356 | | | | | | | | | | |
| East Steve Reinardy | (651) 755-1581 | | | | | | | | | | |
| Mike Herbst | (651) 775-1018 | | | | | | | | | | |
| West Greg Bohmert | (651) 775-1005 | | | | | | | | | | |
| Mike Amiot | (651) 775-1042 | | | | | | | | | | |
| <p>District 6, Rochester Ken DeCramer, 507-286-7580 Jeff Bale, 507-286-7586 Russ Smith, 507-286-7535 Fax 507-285-7112</p> | <p>Ken Pickett (507) 286-7584 Cell (507) 251-0138</p> | | | | | | | | | | |
| <p>District 7, Mankato Mark Schoeb, 507-304-6186 Scott Swanson, 507-304-6189 Fax 507-304-6191</p> | <p>Mitch Jordahl (507) 304-6187 Cell (507) 380-9619</p> | | | | | | | | | | |
| <p>District 8A, Willmar Jay Jorgensen, 320-214-6345 Fax 320-214-6306 District 8B, Marshall Mark DeAustin, 507-537-2068 Fax 507-537-3802</p> | <p>Jon Vlaminck (320) 214-6348 Cell (320) 894-7409</p> | | | | | | | | | | |

Lbs

| | | |
|--------------------|-----|-------------------------------------------------------------------|
| Bituminous | 35 | Aggregate for Gradation QC/QA |
| | 80 | for each plus #4 Aggregate Type for Quality Testing |
| | 35 | for each minus #4 Aggregate Type for Quality Testing |
| | 80 | for each RAP material for Quality Testing |
| | 10 | RAS (shingles) for Processsed Gradation and Quality Testing |
| | 65 | for Mix Properties (QC/QA) 3 full 6" by 12" cylinder molds for QA |
| | 90 | for TSR (QC/QA) 4 full 6" by 12" cylinder molds for QA |
| | 90 | for Aggregate Specific Gravity QC/QA |
| | - | 1 quart of Asphalt Binder QA |
| | - | 1/2 gallon for Asphalt Emulsion QA |
| Grading & Base | 30 | Aggregate for Gradation (Companion sample from 60 lb split). |
| | 25 | Moisture Density Test - Proctor (Companion from 50 lb split). |
| | 30 | Aggregate Quality/Percent Crushing Test - 1 per source |
| Ready-Mix Concrete | 25 | Gradation 3/4" plus |
| | 10 | Gradation 3/4" minus |
| | 6 | Gradation CA 70 & #7 |
| | 1 | Gradation - Sand (500 g), CA 80, #89. |
| | 4.4 | Moisture Test Coarse Aggregate (2000 g) |
| | 1.1 | Moisture Test Fine Aggregate (500 g) |
| | 50 | Quality 3/4" plus - lab sample |
| | 30 | Quality 3/4" minus - lab sample |
| | 30 | Fine Aggregate - lab sample |
| | 10 | 3/4" Plus for the -200 Coarse Aggregate Test (5000 grams) |
| | 6 | 3/4" Minus for the -200 Coarse Aggregate Test (2500 grams) |
| | 5 | Cement, Blended Cement, Fly Ash |
| | - | 1/2 pint plastic container for admixtures. |